Hot & cold water piping systems made of polypropylene

TECHNICAL MANUAL POLO-ECOSAN



PROGRESS / poloplast

TABLE OF CONTENTS

System description

1.1	POLO-ECOSAN Installation system	6
1.1.1	System components	6
1.1.2	Material-related guide values of PP-R	6
1.1.3	Material-related guide values of PP-RCT	7
1.1.4	Fields of application	7
1.1.5	Possible uses	7
1.2	POLO-ECOSAN Pipes	8
1.2.1	Overview	8
1.2.2	POLO-ECOSAN	9
1.2.3	POLO-ECOSAN ML5	10
1.2.4	POLO-UV ML5	12
1.2.5	POLO-ECOSAN ML3	14
1.2.6	Pipe labelling	
1.3	Product line	
	POLO-ECOSAN Pipes	
	POLO-ECOSAN Fittings	
	POLO-ECOSAN Adapters	
	POLO-ECOSAN Fittings and accessories	
1.3.5	POLO-ECOSAN Shut-off devices and accessories	28
	sportation and storage	
2.1	Safety instructions and intended use	35
	king water hygiene	~~
3.1	Drinking water	
3.2	Types of installation	
	Connection of drinking water tapping points	
3.2.2	Fittings for hygienic piping	38
Svet	em requirements	
4 .1	Standards and regulations	30
4.1.1	Planning of drinking water installation systems	
4.1.1		
4.1.2	Terms used	
4.2	1611113 0360	40

4.2	Terms used	40
4.2.1	Standard dimension ratio	40
4.2.2	Pipe series number S	40
	Nominal pressure (PN)	
4.3	Requirements on pipe systems	41
4.3.1	Classification of operational conditions	41
4.3.2	Table of working pressure is exposed	42
4.3.3	Stress that a pipe system is exposed	43
4.4	Chemical resistance	44
4.5	Disinfection	45
4.5.1	Thermal disinfection	45
4.5.2	Chemical disinfection – "Shock disinfection"	46
4.5.3	Continuous metered addition of chemicals – "Permanent disinfection"	46

TABLE OF CONTENTS

Planning and design

5.1	Dimensioning of drinking water systems	. 47
	Differentiating calculation procedure	
5.1.2	Minimum flow pressures of tapping points	. 48
5.1.3	Peak flow rate according to DIN 1988	. 49
5.1.4	Single resistance values z	. 51
	Pressure loss tables	
5.2	Simplified procedure	. 60

Welding technology

6.1	Basic information	.63
6.1.1	Socket welding using a heated tool	.63
6.1.2	Guidelines	.63
6.2	Processing information for welding	.64
6.2.1	Socket welding with a hand-held welding device, from 20 mm	.65
6.2.2	Socket welding with a stationary welding machine, from 40 mm	.66
6.2.3	Welding saddle for 40-250 mm	. 67
6.2.4	Repair plugs	.68
6.2.5	Use of electric welding sockets	. 69
6.2.6	Butt welding machine for 160 mm and above	. 71

Assembly guidelines

7.1	Fastening techniques	. 72
7.1.1	Fixed points	. 72
7.1.2	Sliding points	. 72
7.2	Mounting distances	. 73
7.3	Laying the pipes	. 74
7.4	Length variation	
7.5	Thermal expansion force	. 77
7.6	Expansion compensation	. 78
7.6.1	Bending legs	. 78
7.6.2	Expansion loop	. 79
	Pre-tensioning	
7.7	Insulation	. 80
7.7.1	Hot water insulation	
7.7.2	Cold water insulation	. 81
7.7.3	Dew point	. 81
7.8	Noise protection	
7.9	Fire protection	. 84

TABLE OF CONTENTS

Initial operation

8.1	Pressure-tests	85
8.2	Flushing the system	. 88
8.3	Initial operation	. 88

Quality management

9.1	Quality assurance	.90
9.1.1	Approvals	. 92
9.1.2	Testing institutes for product monitoring and certification	.92
9.2	POLO-ECOSAN Letter of guarantee	.93
9.3	POLO-UV ML5 Letter of guarantee	.94
9.4	Sustainability	.95

General information

The information provided in this technical manual is intended to help you select our products for your application. Text and images were compiled with utmost care. Nevertheless, errors cannot be entirely excluded. POLOPLAST does not assume legal liability or any other form of liability for erroneous information and its consequences. POLOPLAST is grateful for any suggestions or comments.

We are happy to provide further information – please contact the POLOPLAST Sales Office on +49 (0)8342 / 70 06-0, info@poloplast.com

1.1 POLO-ECOSAN Installation system

The POLO-ECOSAN installation system consists of various pipes designed for various fields of application and guarantees a flawless supply of the most precious of all comestibles: drinking water.

Connection Technique using Heated-Tool Socket Welding

When the pipe and the fitting are welded, their plastic materials fuse together to form a homogeneous, firmly bonded whole. Special tools are used to heat up pipe and fitting, which are then just joined together. This connection is reliable and lastingly leakproof.

1.1.1 System components

1.1.1.1 Fittings

The PP-R-metal connection of the POLO-ECOSAN fittings excels by its leakproofness and resistance to torsion. This connection withstands decades of operational loads without any difficulty. Thanks to the specific geometry of their inserts, which are made of high-grade brass, the moulded parts meet the highest safety standards and guarantee safe laying.



The metal threads of the POLOPLAST brass components meet the requirements of the DIN EN 10226 standard and are manufactured from high-quality brass. Moreover, the material complies with the current version of the recommendations (as at 2014) of the Federal Environment Agency on "Materials suitable from a drinking water hygiene point of view". This guarantees that the limit values of the "Deutsche Trinkwasserverordnung (TrinkwV 2001)" (German Drinking Water Ordinance) are reliably observed. All POLO-ECOSAN fittings are compatible with all POLO-ECOSAN pipes (refer to page 8 and following).

1.1.1.2 Pipes and fittings

All pipes and fittings of the POLO-ECOSAN installation system are made of PP-R, with only high-quality raw materials being used. This raw material is equipped with high-grade stabilizers. The stabilizer package protects the polymer from oxidation, which may occur, for example, following long-term exposure to high temperatures > 70 °C and high pressure.

1.1.2 Material-related guide values of PP-R

Properties	Measuring method	Unit	Value
Density	ISO 1183	kg/m³	898
Melt Flow Rate 230 °C/2.16 kg	ISO 1133	g/10 min.	0.3
Modulus of Elasticity in Tension (1mm/min)	ISO 527	MPa	900
Tensile Stress at Yield (50 mm/min)	ISO 527	Мра	28
Charpy Impact Strength, notched (+23 °C)	ISO 179	kJ/m²	25
Coefficient of linear expansion	DIN 53752	mm/mK	0.15
Thermal conductivity	DIN 52612	W/mK	0.24
Pipe surface roughness k		mm	0.007
Specific heat at 20 °C	Calorimeter	KJ/kg K	2.0

ASSEMBLY GUIDELINES

INITIAL OPERATION

QUALITY MANAGEMENT

6.

1.1.3 Material-related guide values of PP-RCT

Properties	Measuring method	Unit	Value
Density	ISO 1183	kg/m³	905
Melt Flow Rate 230 °C/2.16 kg	ISO 1133	g/10 min.	0.3
Modulus of Elasticity in Tension (1mm/min)	ISO 527	MPa	900
Tensile Stress at Yield (50 mm/min)	ISO 527	MPa	25
Charpy Impact Strength, notched (+23 °C)	ISO 179	kJ/m²	40
Coefficient of linear expansion	DIN 53752	mm/mK	0.15
Thermal conductivity	DIN 52612	W/mK	0.24
Pipe surface roughness k		mm	0.007
Specific heat at 20 °C	Calorimeter	KJ/kg K	2.0

1.1.4 Fields of application

For more than 30 years, polypropylene has been successfully used in supply lines of buildings in many countries worldwide. The combination of such excellent properties as chemical resistance, homogeneous connection, resistance to pressure and easy laying make it a reliable and lasting system suitable for various applications. In many countries it is gradually replacing such traditional materials as copper and galvanized steel.

Properties of POLO-ECOSAN

- Enormous durability thanks to high-quality materials and processing
- Homogeneous connection guarantees high operational reliability.
- High demands for hygiene guarantee perfect water quality.
- Good thermal load capacity, therefore high operational reliability.
- High chemical resistance guarantees high durability.
- Minor flow noise makes living highly comfortable.
- High dimensional accuracy and low weight, therefore time- and cost-saving pipe laying.

1.1.5 Possible uses

The POLO-ECOSAN installation system fulfils a variety of demands made on supply lines. It is suitable for universal use in:

- New buildings
- Refurbishment
- Repairs;

in **drinking water installations** for cold and hot water pipes in residential buildings, hospitals, hotels, office buildings, schools, etc., for example:

- Service connections
- Boiler connections
- Water distributing systems
- Rising lines
- Floor-level distribution
- Fittings

as well as piping networks for:

- Rainwater systems
- Outside pipe laying

- Compressed air systems
- Agriculture and horticulture
- Industries, for example the transportation of aggressive media (acids, alkaline solutions, etc.), taking into account its resistance to chemical agents
- Heating installations
- Shipbuilding
- Further media and possible applications upon request.

POLO-ECOSAN is not suitable for:

- Industrial gases
- Flammable liquids and gases
- Coolants/refrigerants

1.2 POLO-ECOSAN Pipes

1.2.1 Overview

POLO-ECOSAN, the high-grade installation pipe made of polypropylene, POLO-ECOSAN ML5, POLO-ECOSAN ML3 and POLO-UV ML5, the multilayer fibre-reinforced composite pipes, guarantee reliable, durable and flawless supply in installation systems.

Wall thickness, pipe material and temperature range are the factors that decide the level of the resistance of a plastic pipe system to pressure.

POLOPLAST pipes are available in various wall thicknesses:

		Product range overview POLO-ECOSAN pipes											
Diameter (d) mm	20	25	32	40	50	63	75	90	110	125	160	200	250
POLO-ECOSAN SDR 6													
POLO-ECOSAN SDR 11													
POLO-ECOSAN ML5 SDR 7.4													
POLO-ECOSAN ML3 SDR 11													
POLO-UV ML5 SDR 7.4													

Pipes 20 - 125 mm = socket welding Pipes 160 - 250 mm = butt welding









POLO-ECOSAN

POLO-ECOSAN ML5

POLO-ECOSAN ML3 POLO-UV ML5

POLOPLAST pipes made of PP-R and PP-RCT are manufactured according to DIN EN ISO 15874, EN ISO 21003 and DIN 8077/78 and fulfil their quality requirements.

DRINKING WATER HYGIENE

WELDING TECHNOLOGY

INITIAL OPERATION

1.2.2 POLO-ECOSAN

The traditional POLO-ECOSAN mono-pipe is made of PP-R.

1.2.2.1 Properties of the material

The physical and chemical properties have been chosen to meet the specific demands of drinking water systems.

Regular testing by in-house and external monitoring guarantee its suitability for various kinds of application.

1.2.2.2 Specification

Material: PP-R (Polypropylene-Random)

Pipe series: SDR 6 / S 2.5 colour: green with a red stripe SDR 11 / S 5.0 colour: green with a blue stripe

Classification of operational conditions: application class according to EN ISO 15874

- SDR 6: class 1/10 bar, class 2/8 bar
- SDR 11: class 1/6 bar, class 2/4 bar

For information on SDR and operational conditions, see page 39/40.

Coefficient of linear expansion: α 0.15 mm/mK

1.2.2.3 Advantages

- Homogeneous connection
- Quick and easy assembly
- Resistance to corrosion
- Neutral in taste and odour
- Smooth pipe inner surface
- Good heat and sound insulation properties

1.2.3 POLO-ECOSAN ML5

The POLO-ECOSAN ML5 pipe represents a milestone in PP-R development. A 5-layer fibre pipe made of PP-R with glass fibre and the PP-RCT material.

1.2.3.1 Properties of the material


PP-RCT: Polypropylene random copolymer with modified crystalline structure and increased resistance to elevated temperatures. This material represents a new generation of the tried and tested PP-R material. Especially with higher temperatures, the increased crystallinity of PP-RCT provides an improved creepdepending-on-time behaviour under internal compression.

- PP = polypropylene
- R = random
- C = crystallinity
- T = temperature

This is why pipes made from this material can have thinner walls and consequently larger inner diameters. Designers and plumbers are offered convincing advantages from this circumstance. Thanks to the larger inner diameter, the hydraulic capacity of the pipes increases, which is specifically advantageous in systems that need to transport large amounts of water, for example in high-rise buildings.

Pipes made of PP-RCT are accepted according to the EN ISO 15874 standard and the EN ISO 21003 standard on multilayer pipes, and represent the state of the art. The same well-tried connection technique is used for pipes and fittings made of PP-RCT as for PP-R pipes.

1.2.3.2 Distribution of layers



1. Exterior PP-R layer

The exterior layer made of high-grade PP-R provides the colour code and guarantees flawless and reliable welding of pipe and fitting.

2. Second exterior layer made of HPCE, a special POLOPLAST compound material

This PP-R glass fibre compound material has been specially developed by POLOPLAST Polymer Engineering and represents the result of many years of research in this field. The perfect connection of glass fibre and PP-R provides excellent linear expansion, deformation properties, as well as good resistance to impact loads at low temperatures.

3. Central layer made of PP-RCT

PP-RCT is a polypropylene random copolymer with a modified crystalline structure. This material improves the long-term behaviour during longer operational periods, particularly, at increased temperatures.

4. Second inner layer made of HPCE, the special POLOPLAST compound material

This layer also provides excellent properties, such as linear expansion, deformation and good resistance to impact load at low temperatures.

5. Inner layer made of PP-RCT

In the same way as the central layer, this layer guarantees improved long-term behaviour during longer operational periods at increased temperatures. Smooth pipe inner surfaces prevent sediments and incrustations.

INITIAL OPERATION

QUALITY MANAGEMENT

1.2.3.3 Specification

Material: PP-R / PP-GF / PP-RCT / PP-GF / PP-RCT

Pipe series: SDR 7.4 / S 3.2 colour: green with silver stripe

Classification of operational conditions: application class according to EN ISO 15874

• SDR 7.4: class 1/8 bar, class 2/8 bar

For information on SDR and operational conditions, see page 39/40.

Coefficient of linear expansion: α 0.038 mm/mK; tested and approved by a third party: OFI Institute, Vienna


1.2.3.4 Advantages

- Lower linear expansion reduced by 75 % as compared to a PP-R standard pipe
- Improved resistance to internal pressure at increased temperatures as compared to a PP-R standard pipe, thanks to the PP-RCT material
- Increased stability allows longer distances between the fastening points
- Increased flow rate increased by approximately 16 % thanks to thinner walls at unchanged dimension and pressure strain
- Higher resistance to impact loads special compound materials increase the resistance to impact loads
- Good chemical resistance thanks to the PP-RCT material

1.2.3.5 Comparison of linear expansion

This comparison distinctly shows the linear expansion caused by temperature changes of a standard PP-R pipe and the POLO-ECOSAN ML5 pipe.

Linear expansion reduces by 75 %.



Comparison of linear expansion values

1.2.4 POLO-UV ML5

The POLO-UV ML5 pipe is a further development of the POLO-ECOSAN ML5 pipe.

1.2.4.1 Properties of the material

The pipe structure has been adopted from the POLO-ECOSAN ML5 pipe, only the exterior layer has been modified. Thanks to this UV resistant layer, this pipe is particularly suitable for laying of supply lines in outdoor areas, for example, in drinking water systems, irrigation systems, heating and cooling water systems.

1.2.4.2 Distribution of layers



1. Exterior PP-R UV layer

The first layer provides UV protection and is made of specially stabilised PP-R to make the pipe highly reliable and resistant to ageing caused by UV radiation.

2. Second exterior layer made of HPCE, the special POLOPLAST compound material

This PP-R glass fibre compound material has been specially developed by POLOPLAST Polymer Engineering and represents the result of many years of research in this field. The perfect connection of glass fibre and PP-R provides excellent linear expansion, deformation properties, as well as good resistance to impact loads at low temperatures.

3. Central layer made of PP-RCT

PP-RCT is a polypropylene random copolymer with a modified crystalline structure. This new material improves the long-term behaviour during longer operational periods, particularly, at increased temperatures.

4. Second inner layer made of HPCE, a special POLOPLAST compound material

This layer also provides excellent properties, such as linear expansion, deformation and good resistance to impact load at low temperatures.

5. Inner layer made of PP-RCT

In the same way as for the central layer, we guarantee improved long-term behaviour of this layer during longer operational periods at increased temperatures. Smooth pipe inner surfaces prevent sediments and incrustations.

1.2.4.3 Processing

The pipes are installed using the existing fittings programme, without any additional operations. The POLO-UV ML5 pipe can be welded directly, with no need of peeling off the outer layer. Thus, pipes and fittings can be installed in the usual simple and safe way.

The fittings of the POLO-ECOSAN product line using the green colour are not long-term resistant to UV light. Suitable measures need to be taken separately to protect them.

1.2.4.4 Specification

Material: PP-R UV / PP-GF / PP-RCT / PP-GF / PP-RCT

Pipe series: SDR 7.4 / S 3.2 colour: black

Classification of operational conditions: application class according to EN ISO 15874

• SDR 7.4: class 1/8 bar, class 2/6 bar

For information on SDR and operational conditions, see page 39/40.

Coefficient of linear expansion: α 0.038 mm/mK; tested and approved by the external OFI Institute, Vienna



1.2.4.5 Advantages

- 10 years of warranty on resistance to UV radiation has been confirmed by a third party
- No additional operations required usual and safe homogeneous welding of pipe and moulded part
- Low linear expansion reduced by 75 % as compared to a PP-R standard pipe
- Increased stability allows longer distances between the fastening points
- Increased flow rate increased by approximately 16 % thanks to thinner walls, with the dimensions and the pressure strain remaining unchanged.
- Higher resistance to impact loads special compound materials increase the resistance to impact loads

1.2.4.6 Examined Resistance to UV Radiation

The resistance of the POLO-UV ML5 pipe to UV radiation has been tested by an acknowledged testing laboratory. During the entire test period samples were taken at certain intervals, which were then subjected to strength tests to examine them for possible changes of the material's mechanical properties. At the same time, material stability tests were carried out on a regular basis. The radiation intensity used for these tests was the same as in Aswan / Egypt over a period of more than 10 years.

DRINKING WATER HYGIENE

1.2.5 POLO-ECOSAN ML3

The POLO-ECOSAN ML3 fibre compound pipe represents an addition to the comprehensive product line with larger dimensions starting from 125 mm and using the tried and tested 3-layer technology.

1.2.5.1 Distribution of layers



1. External layer made of PP-R-CT

The outer layer made of high-grade polypropylene granulate protects the pipe from surface damage resulting from mechanical external forces.

2. Intermediate layer made of PP-RCT-glass fibre compound

The fibre reinforcement in the intermediate layer increases the stability and, in combination with the other two layers, provides low deflection, reduced linear expansion, a high load carrying capacity, increased robustness and resistance to pressure.

3. Internal layer made of PP-RCT

Used as material for the internal layer, high-grade polypropylene granulate not only provides for high temperature resistance, but also ensures the pipe's resistance to corrosion, pitting, leaching and mechanical abrasion.

1.2.5.2 Specification

Material: PP-RCT / PP-RCT GF / PP-RCT

Pipe series: SDR 11 / S 5 colour: green

Classification of Operational Conditions: application class according to EN ISO 15874 • SDR 11: class 1/6 bar, class 2/6 bar

For information on SDR and operational conditions, see page 39/40.

Coefficient of linear expansion: α 0.05 mm/mK

1.2.5.3 Advantages

- Low linear expansion
- Optimal stability
- Minor sagging
- Good chemical resistance thanks to the PP-RCT material
- As compared to a PP-R standard pipe, the PP-RCT material ensures an improved resistance to internal pressure at increased temperatures.

WELDING TECHNOLOGY

INITIAL OPERATION

1.2.6 Pipe labelling

The pipes must be durably labelled in the following way: Example:

Outer diameter \times wall thickness	25 × 4.2
Product name	POLO-ECOSAN
Designation of material	PP-R
SDR wall thickness ratio	SDR 6
Pipe series S	S 2.5
Dimensional class according to EN ISO 15874	A
Class of application and admissible operational pressure according to EN ISO 15874	Class 1/10 bar, Class 2/8 bar
Range of use	20 bar/20C, 10 bar/70C
Suitability for drinking water	TW
Impermeability to light	opaque
Product standards	DIN 8077/8078, EN ISO 15874
Certificates, approvals	SKZ A 553
Material labelling	Material
Machine number	Machine
Date of manufacture	DAY MONTH YEAR HOUR:MINUTE
Manufacturer	POLOPLAST

Imprint and order:

25×4.2 **POLO-ECOSAN MADE IN GERMANY**

PP-R SDR 6/S 2.5 A Class 1/10 bar Class 2/8 bar 20 bar/20C 10 bar/70C TW opaque DIN 8077/78 EN ISO 15874 SKZ A 553 Material Machine Day Month Year Hour:Minute

. 15

1.3 Product line

1.3.1 POLO-ECOSAN Pipes

POLO-ECOSAN Pipe SDR 6 / S 2.5 PP-R for hot and cold water acc. to

DIN 8077/78 and EN ISO 15874, class 1/10 bar, class 2/8 bar, SKZ certificate A 553, colour green with red line



A. no.	Outer Ø mm	Wall thick- ness mm	Inner Ø mm	DN	Water Content I/m	Weight kg/m	Packing unit parcel/bar	Avail- ability
16002	20	3.4	13.2	12	0.137	0.172	100 m / 4 m	S
16003	25	4.2	16.6	15	0.216	0.266	60 m / 4 m	S
16004	32	5.4	21.2	20	0.353	0.434	40 m / 4 m	S
16005	40	6.7	26.6	25	0.556	0.671	20 m / 4 m	S
16006	50	8.3	33.4	32	0.866	1.040	20 m / 4 m	S
16007	63	10.5	42.0	40	1.385	1.650	12 m / 4 m	S
16008	75	12.5	50.0	50	1.936	2.340	8 m / 4 m	S
16009	90	15.0	60.0	-	2.827	3.360	4 m / 4 m	S
16010	110	18.3	73.4	65	4.208	5.010	4 m / 4 m	S

POLO-ECOSAN Pipe SDR 11 / S 5 PP-R for hot and cold water acc. to DIN 8077/78 and EN ISO 15874, class 1/6 bar, class 2/4 bar, colour green with blue line



A. no.	Outer Ø mm	Wall thick- ness mm	Inner Ø mm	DN	Water Content I/m	Weight kg/m	Packing unit parcel/bar	Avail- ability
16102	20	1.9	16.2	15	0.206	0.107	100 m / 4 m	S
16103	25	2.3	20.4	20	0.327	0.164	60 m / 4 m	S
16104	32	2.9	26.2	25	0.531	0.261	40 m / 4 m	S
16105	40	3.7	32.6	32	0.834	0.412	20 m / 4 m	S
16106	50	4.6	40.8	40	1.307	0.638	20 m / 4 m	S
16107	63	5.8	51.4	50	2.075	1.010	12 m / 4 m	S
16108	75	6.8	61.4	-	2.941	1.410	8 m / 4 m	S
16109	90	8.2	73.6	65	4.254	2.030	4 m / 4 m	S
16110	110	10.0	90.0	80	6.362	3.010	4 m / 4 m	S

POLO-ECOSAN ML5 Fibre Pipe SDR 7.4 / S 3.2 PP-R, PP-RCT for	A. no.	Outer Ø mm	Wall thick- ness mm	Inner Ø mm	DN	Water Content I/m	Weight kg/m	Packing unit parcel/bar	Avail- ability
hot and cold water acc. to DIN 8077/78 and EN ISO 15874, class 1/8 bar, class	16322	20	2.8	14.4	15	0.163	0.149	100 m / 4 m	S
2/8 bar. SKZ certificate A 634. colour	16323	25	3.5	18.0	20	0.254	0.236	60 m / 4 m	S
green with silver line	16324	32	4.4	23.2	25	0.423	0.385	40 m / 4 m	S
	16325	40	5.5	29.0	32	0.661	0.584	20 m / 4 m	S
	16326	50	6.9	36.2	40	1.029	0.916	20 m / 4 m	S
	16327	63	8.6	45.8	50	1.647	1.474	12 m / 4 m	S
	16328	75	10.3	54.4	-	2.324	2.048	8 m / 4 m	S
	16329	90	12.3	65.4	65	3.359	2.922	4 m / 4 m	S
	16330	110	15.1	79.8	80	5.001	4.374	4 m / 4 m	S

POLO-ECOSAN ML3 Fibre Pipe SDR 11 / S 5 PP-RCT for hot and cold water acc. to DIN 8077/78 and EN ISO 15874, class 1/6 bar, class 2/6 bar, colour green with silver line



	A. no.	Outer Ø mm	Wall thick- ness mm	Inner Ø mm	DN	Water Content I/m	Weight kg/m	Packing unit parcel/bar	Avail- ability
EN bar.	16332	125	11.4	102.2	100	8.200	4.065	4 m / 4 m	MQ
ai,	16333	160*	14.6	130.8	125	13.440	6.645	4 m / 4 m	MQ
	16334	200*	18.2	163.6	150	21.031	10.230	4 m / 4 m	MQ
	16335	250*	22.7	204.6	200	32.865	16.125	4 m / 4 m	MQ

DN: Nominal Diameter (Approximate inner diameter as a dimensionless standard designation for piping and fittings)

S = Standard-Range stored, MQ = Minimum order quantity in pieces or meter

* Butt Welding

16 .

SYSTEM DESCRIPTION

POLO-UV ML5 Fibre Pipe with UV protection layer, SDR 7.4 / S 3.2 / PP-R /PP-RCT for hot and cold water acc. to DIN 8077/78 and EN ISO 15874, class 1/8 bar, class 2/6 bar, colour black

A. no.	Outer Ø mm	Wall thick- ness mm	Inner Ø mm	DN	Water Content I/m	Weight kg/m	Packing unit parcel/bar	Avail- ability
40322	20	2.8	14.4	15	0.163	0.149	100 m / 4 m	S
40323	25	3.5	18.0	20	0.254	0.236	60 m / 4 m	S
40324	32	4.4	23.2	25	0.423	0.385	40 m / 4 m	S
40325	40	5.5	29.0	32	0.661	0.584	20 m / 4 m	S
40326	50	6.9	36.2	40	1.029	0.916	20 m / 4 m	S
40327	63	8.6	45.8	50	1.647	1.474	12 m / 4 m	S





A. no.	Diameter (d) mm	Packing unit parcel/bar
14902	20	75 / 3 m
14903	25	75 / 3 m
14904	32	75 / 3 m
14905	40	15 / 3 m
14906	50	15 / 3 m
14907	63	15 / 3 m
14908	75	15 / 3 m
14909	90	15 / 3 m
14910	110	15 / 3 m

1.3.2 POLO-ECOSAN Fittings

POLO-ECOSAN Long cross-over section	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	16502	20	150 / 10	S
	16503	25	100 / 10	S
	16504	32	70 / 10	S
	16506	40	25 / 5	MQ

POLO-ECOSAN Short cross-over section A. no.



A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
17502	20	10	S
17503	25	10	S

2	QUALITY	IANAGEMENT
		ž

OLO-ECOSAN Welding socket	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17002	20	600 / 10	S
	17003	25	400 / 10	S
	17004	32	250 / 10	S
	17005	40	170 / 10	S
	17006	50	100 / 5	S
	17007	63	50 / 1	S
	17008	75	40 / 1	S
	17009	90	24 / 1	S
	17010	110	15 / 1	S
	17011	125	12 / 1	MQ

POLO-ECOSAN Reducer male / female	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17603	25 / 20	300 / 10	S
	17605	32 / 20	250 / 10	S
	17606	32 / 25	200 / 10	S
	17608	40 / 20	400 / 5	S
	17609	40 / 25	300 / 5	S
	17610	40 / 32	200 / 5	S
	17612	50 / 20	250 / 5	S
	17613	50 / 25	150 / 5	S
	17614	50 / 32	200 / 5	S
	17615	50 / 40	150 / 5	S
	17618	63 / 25	100 / 1	S
	17619	63 / 32	120 / 1	S
	17620	63 / 40	100 / 1	S
	17621	63 / 50	75 / 1	S
	17627	75 / 50	50 / 1	S
	17628	75 / 63	50 / 1	S
	17634	90 / 50	40 / 1	S
	17635	90 / 63	40 / 1	S
	17636	90 / 75	30 / 1	S
	17643	110 / 63	30 / 1	S
	17644	110 / 75	25 / 1	S
	17645	110 / 90	20 / 1	S
	17646	125 / 110	15 / 1	MQ

POLO-ECOSAN Reducer male, butt welding						
	PP-RCT, SDR 11					



17647/2 160/110 10/1	
1704772 1007110 1071 1	MQ
17648/2 160/125 10/1 1	ИQ
17650/2 200/160 5/1 I	ИQ
17652/2 250/200 1/1 !	ИQ

POLO-ECOSAN Welding elbow 90°	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17042	20	500 / 10	S
	17043	25	300 / 10	S
	17044	32	150 / 10	S
	17045	40	100 / 5	S
	17046	50	50 / 5	S
	17047	63	25 / 1	S
	17048	75	15 / 1	S
	17049	90	12 / 1	S
	17050	110	12 / 1	S
	17051	125	8 / 1	MQ

POLO-ECOSAN Butt welding elbow 90°	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
PP-RCT, SDR 11	17053 / 2	160	1/1	MQ
	17055 / 2	200	1/1	MQ
	17057 / 2	250	1/1	MQ

POLO-ECOSAN Welding elbow 45°	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability	
	17102	20	200 / 10	S	
	17103	25	150 / 10	S	
	17104	32	100 / 10	S	
	17105	40	50 / 5	S	
	17106	50	25 / 5	S	
	17107	63	12 / 1	S	
	17108	75	20 / 1	S	
	17109	90	15 / 1	S	
	17110	110	8/1	S	
	17111	125	5/1	MQ	
POLO-ECOSAN Butt welding elbow 45°			Supply unit oard	Avail	

POLO-ECOSAN Butt welding elbow 45°	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
PP-RCT, SDR 11	17113/2	160	1/1	MQ
	17115/2	200	1/1	MQ
	17117 / 2	250	1/1	MQ

SYSTEM DESCRIPTION

. 19

POLO-ECOSAN Welding tee	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17202	20	300 / 10	S
	17203	25	200 / 10	S
	17204	32	100 / 10	S
	17205	40	30 / 5	S
	17206	50	30 / 2	S
	17207	63	10 / 1	S
	17208	75	15 / 1	S
	17209	90	12 / 1	S
	17210	110	6/1	S
	17211	125	5/1	MQ

POLO-ECOSAN Butt welding tee	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
PP-RCT, SDR 11	17213 / 2	160	1/1	MQ
	17215 / 2	200	1/1	MQ
100	17217 / 2	250	1/1	MQ

Reduced tee on request

POLO-ECOSAN Reduced welding tee



A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
17250	$25 \times 20 \times 20$	250 / 10	S
17251	$20 \times 25 \times 20$	250 / 10	MQ
17254	25 × 20 × 25	250 / 10	S
17256	25 × 25 × 20	250 / 10	MQ
17261	$32 \times 20 \times 20$	120 / 5	MQ
17267	32 × 20 × 25	120 / 5	MQ
17273	$32 \times 20 \times 32$	120 / 5	S
17275	$32 \times 25 \times 32$	120 / 5	S
17305	$40 \times 20 \times 40$	80 / 5	S
17307	$40 \times 25 \times 40$	80 / 5	S
17309	$40 \times 32 \times 40$	80 / 5	S
17311	$50 \times 20 \times 50$	40 / 2	MQ
17334	$50 \times 25 \times 50$	40 / 2	S
17336	$50 \times 32 \times 50$	40 / 2	S
17338	$50 \times 40 \times 50$	40 / 2	S
17340	$63 \times 20 \times 63$	25 / 1	S
17352	$63 \times 25 \times 63$	25 / 1	S
17354	$63 \times 32 \times 63$	25 / 1	S
17356	$63 \times 40 \times 63$	25 / 1	S
17358	$63 \times 50 \times 63$	25 / 1	S
17360	75 × 20 × 75	15 / 1	MQ
17370	75 × 25 × 75	15 / 1	S
17372	75 × 32 × 75	15 / 1	S
17374	75 × 40 × 75	15 / 1	S
17376	$75 \times 50 \times 75$	15 / 1	S
17378	$75 \times 63 \times 75$	15 / 1	S
17394	$90 \times 50 \times 90$	12 / 1	MQ
17396	$90 \times 63 \times 90$	12 / 1	S
17398	$90 \times 75 \times 90$	8 / 1	S
17414	110 × 63 × 110	14 / 1	S
17416	110 × 75 × 110	6 / 1	S
17418	110 × 90 × 110	6 / 1	S
17420	125 × 110 × 125	6 / 1	MQ

Weld-in saddle Material: PP-R

Colour: Green Standards: EN ISO 15874 Product line: Ø 40–250 mm Processing: Socket welding



A	A. no.	Diameter (d) Pipe/outlet mm	Drill dia- meter mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
1	7741	40/20	25	0.014	250/5	S
1	7742	40/25	25	0.016	250/5	S
1	7744	50/20	25	0.014	250/5	S
1	7745	50/25	25	0.016	250/5	S
1	7747	63/20	25	0.014	200/5	S
1	7748	63/25	25	0.016	200/5	S
1	7749	63/32	32	0.027	150/5	S
1	7750	75/20	25	0.014	200/5	S
1	7751	75/25	25	0.016	200/5	S
1	7752	75/32	32	0.027	120/5	S
1	7754	90/20	25	0.014	200/5	S
1	7756	90/25	25	0.017	200/5	S
1	7758	90/32	32	0.028	150/5	S
1	7760	110/20	25	0.015	200/5	S
1	7761	110/25	25	0.017	150/5	S
1	7762	110/32	32	0.028	100/5	S
1	7765	125/20	25	0.015	200/5	S
1	7766	125/25	25	0.017	150/5	S
1	7767	125/32	32	0.028	100/5	S
1	7770	160-250/20	25	0.015	200/5	S
1	7771	160-250/25	25	0.017	200/5	S
1	7772	160-250/32	32	0.028	100/5	S
1	7773	160-250/40	40	0.037	200/5	S
1	7774	160-250/50	50	0.048	100/5	S
1	7775	160-250/63	63	0.071	50/1	S

Weld-in saddle female thread
Material: PP-R/brass
Colour: Green

Colour: Green Standards: EN ISO 15874 Product line: Ø 40–250 mm Processing: Socket welding



A. no.	Diameter (d) Pipe/outlet mm	Drill dia- meter mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
18352	40 × 1/2"	25	0.113	100/5	S
18353	40 × 3/4"	25	0.138	100/5	S
18354	50 × 1/2"	25	0.028	100/5	S
18355	50 × 3/4"	25	0.137	100/5	S
18356	63 × 1/2"	25	0.113	100/5	S
18357	63 × 3/4"	25	0.138	50/5	S
18358	63 × 1"	32	0.218	50/5	S
18359	75 × 1/2"	25	0.113	80/5	S
18360	75 × 3/4"	25	0.034	80/5	S
18361	75 × 1"	32	0.219	50/5	S
18362	90 × 1/2"	25	0.114	80/5	S
18363	90 × 3/4"	25	0.139	80/5	S
18364	90 × 1"	32	0.219	50/5	S
18366	110 × 1/2"	25	0.114	100/5	S
18367	110 × 3/4"	25	0.139	80/5	S
18368	110 × 1"	32	0.221	50/5	S
18370	125 × 1/2"	25	0.113	50/5	S
18371	125 × 3/4"	25	0.139	50/5	S
18372	125 × 1"	32	0.218	50/5	S
18375	160–250 × 1/2"	25	0.113	100/5	S
18376	160–250 × 3/4"	25	0.140	50/5	S
18377	160–250 × 1"	32	0.220	50/5	S

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

QUALITY MANAGEMENT

POLO-ECOSAN End cap	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17702	20	400 / 10	S
	17703	25	250 / 10	S
	17704	32	150 / 10	S
	17705	40	100 / 5	S
	17706	50	60 / 5	S
	17707	63	30 / 1	S
	17708	75	20 / 1	S
	17709	90	30 / 1	S
	17710	110	15 / 1	S
	17711	125	12 / 1	MQ

POLO-ECOSAN End cap PP-RCT. SDR 11	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
PP-RCI, SDR II	17712/2	160	1	MQ
	17713/2	200	1	MQ
	17714/2	250	1	MQ

POLO-ECOSAN Flange bushing with gasket	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	17807	63	30 / 1	MQ
	17808	75	20 / 1	S
	17809	90	15 / 1	S
	17810	110	12 / 1	S
	17811	125	10 / 1	S

POLO-ECOSAN Flange bushing with gasket	A. no.	D
PP-RCT, SDR 11	17812/2	
	17814/2	
	17816/2	

A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
17812/2	160	1	S
17814/2	200	1	S
17816/2	250	1	S

* 125–250, can be used for butterfly valves

POLO-ECOSAN PP-flange, glass fibre reinforced, for flange bushing PN 16	A. no.	Diameter (d) mm	DN	Supply unit card- board box/package	Avail- ability
3	14207	63	50	1	S
	14208	75	65	1	S
3 3	14209	90	80	1	S
	14210	110	100	1	S
2	14211	125	100	1	S
•	14212	160	150	1	S
	14214	200	200	1	S
	14216	250	250	1	S

QUALITY MANAGEMENT

POLO-ECOSAN Socket for electric welding
Material: PP-RCT
Colour: Green
SDR 7.4
Welding voltage: 8–48 V
Pin size: 4 mm
With bar code
Suitable welding tool A. no. 15270



A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
14802	20	0.045	35 / 1	S
14803	25	0.055	25 / 1	S
14804	32	0.075	20 / 1	S
14805	40	0.110	25 / 1	S
14806	50	0.155	20 / 1	S
14807	63	0.225	25 / 1	S
14808	75	0.330	36 / 1	S
14809	90	0.490	18 / 1	S
14810	110	0.800	15 / 1	S
14811	125	1.060	1/1	S
14812	160	1.855	1/1	S
14814	200	4.100	1/1	S
14816	250	6.550	1/1	S

1.3.3 POLO-ECOSAN Adapters

POLO-ECOSAN Adapter female, not for wrench	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18104	20 × 1/2"	130 / 10	S
	18105	20 × 3/4"	100 / 10	MQ
	18106	25 × 1/2"	130 / 10	S
	18107	25 × 3/4"	100 / 10	S
	18108	32 × 3/4"	100 / 10	S

POLO-ECOSAN Adapter female for wrench	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18109	32 × 1"	50 / 5	S
	18110	40 × 1"	50 / 5	MQ
	18111	40 × 1 1/4"	30 / 5	S
	18112	50 × 1 1/4"	30 / 5	MQ
	18113	50 × 1 1/2"	25 / 5	S
	18115	63 × 2"	10 / 1	S
	18116	75 × 2"	8/1	MQ
	18117	75 × 2 1/2"	8/1	S
		·	Other size	es on request

POLO-ECOSAN Adapter male, not for wrench Supply unit card-Avail-A. no. Diameter (d) mm board box/package ability 20 × 1/2" S 18154 100 / 10 18155 $20 \times 3/4"$ 100 / 10 MQ 25 × 1/2" S 18156 100 / 10 18157 $25 \times 3/4"$ 100/10 S 18158 $32 \times 3/4"$ 80/5 S

INITIAL OPERATION

	24184	32	50 / 1	MQ
	24185	40	25 / 1	MG
	24186	50	20 / 1	MG
•	24187	63	15 / 1	MG

Other sizes on request

Avail-

ability S

MQ

S

MQ S

S

S

S

S

Supply unit card-

board box/package

50/5

50/5

30/5

20/5

20/5

20/1

8/1

6/1

4/1



POLO-ECOSAN Adapter male for wrench

SYSTEM DESCRIPTION

POLO-ECOSAN Elbow adapter female from 1" for wrench	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18204	20 × 1/2"	150 / 10	S
	18205	20 × 3/4"	100 / 10	MQ
	18206	25 × 1/2"	120 / 10	S
	18207	25 × 3/4"	100 / 10	S
	18208	32 × 3/4"	70/5	S
	18200	32 ~ 1"	40 / 10	S

Diameter (d) mm

32 × 1"

 40×1 "

40 × 1 1/4"

50 × 1 1/4"

 $50 \times 1 \ 1/2"$

 $63 \times 2"$

75 × 2 1/2"

90 × 3"

110 × 2 1/2"

	18209	32 × 1"	40 / 10	S
POLO-ECOSAN Elbow adapter male from 1" for wrench	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18254	20 × 1/2"	100 / 10	S
	18256	25 × 1/2"	100 / 10	S
	18257	25 × 3/4"	70 / 10	S
and a second	18258	32 × 3/4"	70 / 5	MQ
	18259	32 × 1"	40 / 5	S

A. no.

18159

18160

18161

18162

18163

18165

18167

18169

18171

POLO-ECOSAN Tee adapter female from 1" for wrench	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18304	$20 \times 1/2" \times 20$	100 / 10	S
	18306	25 × 1/2" × 25	80 / 10	S
	18307	$25 \times 3/4" \times 25$	70 / 10	S
	18311	$32 \times 1/2" \times 32$	40 / 5	S
	18310	$32 \times 3/4" \times 32$	40 / 5	S
	18309	32 × 1" × 32	30 / 5	S
	18312	$40 \times 3/4" \times 40$	30 / 5	MQ

POLO-ECOSAN Screw adapter pipe end/pipe end	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	24182	20	80 / 1	MQ
	24183	25	50 / 1	MQ
	24184	32	50 / 1	MQ
	24185	40	25 / 1	MQ
	24186	50	20 / 1	MQ
V	24187	63	15 / 1	MQ

QUALITY MANAGEMENT

POLO-ECOSAN Screw adapter, male, thread/pipe end	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	24172	20 × 1/2"	80 / 1	MQ
	24173	25 × 3/4"	50 / 1	S
	24174	32 × 1"	50 / 1	MQ
	24175	40 × 11/4"	25 / 1	MQ
C. all	24176	50 × 11/2"	20 / 1	MQ
-	24177	63 × 2"	15 / 1	MQ

POLO-ECOSAN Screwed union plastic/brass F with socket end	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	20043	20 × 1/2"	100 / 1	S
and the second sec	20045	20 × 3/4"	100 / 1	S
	20047	25 × 3/4"	100 / 1	S
	20050	32 × 1"	70 / 1	S
	20053	40 × 1 1/4"	50 / 1	S
	20056	50 × 1 1/2"	30 / 1	S
	20058	63 × 2"	20 / 1	S

1.3.4 POLO-ECOSAN Fittings and accessories



A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
18004	20 × 1/2"	100 / 10	S
18006	25 × 1/2"	80 / 10	S
18007	25 × 3/4"	80 / 10	S

POLO-ECOSAN Double wall union, female, wo outlets	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	18016	25 × 1/2"	80 / 10	S



distances 150 mm

female	A. no.	Diameter (d) mm	Supply unit card- board box/package
	18034	20 × 1/2"	1



POLO-ECOSAN wall union plate,

A. no.	Diameter (d) mm	board box/package
18034	20 × 1/2"	1
18036	25 × 1/2"	1

ASSEMBLY GUIDELINES

Avail-

ability S S

Assembly plate, plastic, with screws for wall union, selectable distances 115 / 140 / 150 / 160 / 180 mm



-1

A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
15484	250 × 45	50 / 1	S

Assembly plate, galvanized	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	15480	2000 × 50 × 3	25 / 1	S
2002				

Assembly unit, galvanized, for wall union, with screws	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
Distance 150 / 80 mm	15482	420 × 60 × 45	1	S
- IF				



1.3.5 POLO-ECOSAN Shut-off devices and accessories

POLO-ECOSAN Shut-off valve, body without discharge screw	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	20304	20 × 3/4"	50 / 5	S
	20306	25 × 3/4"	50 / 5	S
	20308	32 × 1"	30 / 5	S
	20310	40 × 1 1/4"	25 / 1	S

3/4"	125 / 1	S
		U U
1"	75 / 1	S
1 1/4"	40 / 1	S
	1 1/4"	1 1/4" 40 / 1

Concealed valve, upper part in flexible length 60–110 mm	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	14612	3/4"	50 / 1	S
	14614	1"	50 / 1	S




Concealed valve, upper part	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	14611	3/4"	40 / 1	S
	14617	1"	40 / 1	S

Concealed valve, upper part, public authority design	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
	14622	3/4"	60 / 1	S
	14628	1"	40 / 1	S

POLO-ECOSAN Ball valve Handle: glass fibre reinforced	A. no.	Diameter (d) mm	Supply unit card- board box/package	Avail- ability
polyamide, ball and stem: brass	20402	20	50 / 5	S
PTFE seats, NBR O-ring	20403	25	25 / 5	S
	20404	32	15 / 1	S
	20405	40	10 / 1	S
	20412	50	6/1	S
	20414	63	5/1	S
	20416	75	5/1	MQ

INITIAL OPERATION

Assembly plug Material: PP-R	A. no.	Diameter (d) mm	Colour	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
Colour: Blue, Red Product line: Ø 1/2"	15413	1/2"	Red	0.022	200/10	S
FIGUUCI III e. Ø 1/2	15414	1/2"	Blue	0.022	200/10	S





Without welding tools

Working temperature: TFE 260 °C ± 10 °C

Socket welding machine up to Ø 63 mm "basic"	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
Working range: max. Ø 20–63 mm Power supply: 230 V–50/60 Hz	15025	20-63	1.440	1	S
Absorbed power: 500 W Working temperature: TFE 260 °C ± 10 °C Without welding tools					



lout wolding toolo	

SYSTEM DESCRIPTION

TRANSPORTATION AND STORAGE

Socket welding machine up to Ø 125 mm Working range: max. Ø 20-125 mm Power supply: 230 V-50/60 Hz Absorbed power: 1,400 W Working temperature: TFE 260 $^{\circ}\text{C}$ \pm 10 $^{\circ}\text{C}$ Without welding tools



	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
	15015	20–125	3.160	1	S
l					

Socket welding machine for pipes from 40 to 125 mm Product line: Ø 40–125 mm



A. no.	Weight kg/pc.	Supply unit card- board box/package	Availability
15205	50	1	S

Availability

S

Welding gauge Material: PP-R	A. no.	Weight kg/pc.	Supply unit card- board box/package
Colour: Green Product line: Ø 40–125 mm	15030	0.0056	700/50
For marking the welding depth on the pipe			



Butt welding machine for pipes up to 250 mm Working range: max. Ø 75–250 mm	A. no.	Weight kg/pc.	Supply unit card- board box/package	Availability
Power supply: 230 VAC 50/60 Hz Absorbed power: 3,500 W	15207	63	1	S
Working temperature: 210 °C \pm 10 °C				



7. California
R

y: 230 VAC 50/60 Hz ower: 3,500 W	15207	63	1	
perature: 210 °C \pm 10 °C				

WELDING TECHNOLOGY

INITIAL OPERATION

Welding machine for electric fittings Working range: 20–315 mm Power supply: 230 V single phase 50/60 Hz Universal adapter: 4.0–4.7 mm Laser scanner For fittings from 8–48 V	A. no.	Weight kg/pc.	Supply unit card- board box/package	Availability
Universal adapter: 4.0-4.7 mm	15270	25.0	1	S



to prepare	A. no.	Working range	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
ctro-fusion	15167	20-125	1.100	1	S

Rotational pipe scraper

Professional rotary scrapers, essential to prepare the plastic pipes and fittings before electro-fusion welding

Peeling depth: 0.2 mm (0.15-0.25 mm)



Pipe scraper Professional rotary scrapers, essential to prepare	A. no.	Working range	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
the plastic pipes and fittings before electro-fusion welding	15169	90 (SDR 11)- 315 (SDR 17.6)	6.500	1	S

Peeling depth: 0.3 mm (0.25-0.35 mm)



15169	315 (SDR 17.6)	6.500	1	S

Cleaning towels for welded plastic joints 1 can = 100 towels	A. no.	Weight kg/pc.	Supply unit card- board box/package	Availability
Ingredient: Ethanol	15163	-	1	S

Welding set "BASIC 40" with metal case Working range: max. Ø 20-40 mm Power supply: 230 V-50/60 Hz Absorbed power: 500 W With welding tool



SYSTEM DESCRIPTION

TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

SYSTEM REQUIREMENTS

PLANNING AND DESIGN

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

A. no.	Diameter (d)	Weight	Supply unit card-	Avail-
	mm	kg/pc.	board box/package	ability
21310	20-40	-	1	S

Welding set "Professional 63" with metal case Working range: max. Ø 20–63 mm	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
Power supply: 230 V–50/60 Hz Absorbed power: 800 W	15311	20-63	-	1	S
With welding tool and pipe cutter					

Assembly tool "Spider" Universal-purpose welding aid	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
Jniversal-purpose welding aid or socket welding from 63–125 mm	15212	63–125	6.800	1	S



from Ø 20 to 40 mm	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
	15001	20-40	0.460	1	S



Pipe cutter for pipes Material: Metal Colour: Red

Pipe cutter for pipes from Ø 20 to 63 mm Material: Metal	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
Colour: Red	15003	20-63	1.240	1	S



Pipe cutter for pipes from Ø 50 to 110 mm Material: Metal Range of application: for pipes SDR 6/7.4/11

A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability	
15007	50–110	2.0	1	S	



Welding attachment

Material: Aluminium, teflon-coated Standards: according to DVS, type A Product line: Ø 20–125 mm Processing: Socket welding



A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
15042	20	0.100	1	S
15043	25	0.166	1	S
15044	32	0.213	1	S
15045	40	0.268	1	S
15046	50	0.268	1	S
15047	63	0.430	1	S
15048	75	0.668	1	S
15049	90	0.880	1	S
15050	110	1.230	1	S
15051	125	1.520	1	S

Welding tools for weld-in saddle Material: Aluminium, teflon-coated Product line: Ø 40–250 mm Processing: Socket welding



A. no.	Diameter (d) Pipe/outlet mm	Bore dia- meter mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
15065	40	25	0.225	1	S
15066	50	25	0.240	1	S
15067	63	25	0.240	1	S
15082	63	32	0.240	1	S
15068	75	25	0.275	1	S
15083	75	32	0.280	1	S
15069	90	25	0.280	1	S
15084	90	32	0.370	1	S
15070	110	25	0.300	1	S
15085	110	32	0.400	1	S
15071	125	25	0.405	1	S
15086	125	32	0.405	1	S
15087	160	25	0.285	1	S
15088	160	32	0.305	1	S
15106	160-250	40	0.350	1	S
15107	160-250	50	0.652	1	S
15108	160-250	63	1.048	1	S

Hole saw for weld-in saddles Material: Metal

For installation holes and continuous drilling A. no. 15094 necessary



A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
15095	25	-	1	S
15096	32	-	1	S
15097	40	-	1	S
15098	50	-	1	S
15099	63	-	1	S

Quick change system

With pilot drill for hole saw, bayonet catch, quick change between hole saws of different diameters



A. NO.	TOF A. NO.
15094	15095–15099

A. no.

for A. no.

Welding attachment	A. no.	Diameter (d)	Weight	Supply unit card-	Avail-
for repair of holes up to Ø 8 mm		mm	kg/pc.	board box/package	ability
Material: Aluminium, Teflon-coated	15080	8	0.169	1	S



Welding plug for repair of holes up to Ø 8 mm	A. no.	Diameter (d) mm	Weight kg/pc.	Supply unit card- board box/package	Avail- ability
	21090	8	0.003	1200/100	S



SYSTEM DESCRIPTION

TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

SYSTEM REQUIREMENTS

PLANNING AND DESIGN

TRANSPORTATION AND STORAGE

2.1 Safety instructions and intended use

- Carefully read the Technical Manual and the Operating Instructions before starting work.
- POLOPLAST Installation Systems may only be planned, assembled and started up as described in the present manual.
- For any deviating fields of application, make sure to obtain POLOPLAST'S advice.
- All national and international safety regulations and regulations on accident prevention have to be observed.
- Planning, installation and start-up have to be carried out pursuant to the current directives, standards and regulations, as intended and in accordance with the state of the art.
- Only POLOPLAST system components are allowed to be used. The use of other components entails loss of guarantee (refer to the Letter of Guarantee on page 93).
- Observe the general safety regulations when handling assembly tools. Danger of burn.

Handling instructions

- POLOPLAST PP-R / PP-RCT pipes can generally be stored at any ambient temperature.
- Nevertheless, the material must never be subject to impacts or blows, particularly at temperatures below 5 °C.
- Do not drop the pipes when unloading them and protect them from falling objects.
- Select the place of storage so as to make sure that the pipes are always supported over their entire length.
- Before starting assembly, check the pipe and particularly the pipe ends for cracks or damage.
- Observe cleanliness when storing and laying the pipes and fittings. In order to protect the pipes and fittings against contamination, do not remove the packaging material before the material is used.
- Pipes (except UV pipes) and fittings must not be exposed to UV radiation over prolonged periods as this reduces the durability and the special properties of the pipes; provide protection of the pipes from the outside.
- At temperatures below zero, water supply pipes must be protected from frost, and drained, if necessary.
- Cut the pipes using only sharp tools.



Avoid sharp impacts and blows to the pipes, especially at low temperatures. Do not throw when unloading. Protect pipes from falling objects.



Do not use cracked or damaged pipes.



Do not expose pipes to UV-radiation for extended periods of time.



During polyfusion welding, do not twist the pipe or fitting; push the pipe and fitting joint together in a straight manner.



Protect pipes filled with water from freezing.



Put down pipes or pipe bundles carefully. Cover pipes in areas of falling rocks, etc.



Only cut pipes with sharp cutters.



Protect stored pipes from sun and rain.



Minor corrections can only be made during joining.



Drain lines in danger of freezing.

. 35

DRINKING WATER HYGIENE

3.1 Drinking water

Drinking water is our most important comestible, which is why water should always be available in optimum quality. The basic requirements on the quality of drinking water in Germany are defined in the "Drinking Water Ordinance (Trinkwasserverordnung)". To make sure to achieve the required quality parameters, the generally acknowledged codes of practice must also be observed. Drinking water hygiene has always been an important matter, particularly in sensitive buildings such as hospitals or retirement homes. But according to the latest findings, hygiene has also become an important topic for the construction of single- and



two-family houses. In this connection, several requirements must be met by the design of drinking water installations. Only specialised companies should be involved in their planning or modification. They know all the relevant technical aspects and are obliged to adhere to them. The dimensional design of the pipe system, the types of materials used, as well as pipe insulation and minimisation of possible water stagnation in the pipes, are of great significance. Materials in contact with the drinking water may transmit undesirable substances to the drinking water. Improper design and assembly of an installation may also further the formation and growth of biofilm, which establishes optimum conditions for the growth of undesirable microorganisms such as legionellae and pseudomonads. They may become a hazard to the occupants' health. Furthermore, the distance of flow up to the tap should be as short as possible. Dead-water sections in which the water flows only rarely or does not flow at all, need to be avoided by all means.

If the influence of all these factors can be minimized as early as at the planning stage, this will make sure that the interior installations also maintain an optimum water quality. Structural components and materials that are in contact with drinking water must not affect it adversely. Planning and assembly of drinking water installations must also ensure that the comestible drinking water is conveyed under perfect hygienic conditions.

The following lists the most important criteria that need to be observed for perfect planning and assembly of the system and optimum drinking water quality:

- Avoidance of stagnation
- Operation as intended
- Short connecting lines
- Main consumer at the end of the single-connection line
- Separation of sections that are not in use
- Correct dimensioning
- Hydraulic alignment of circulation systems
- Avoidance of cold water heating up (max. 25 °C)
- Avoidance of hot water cooling down (min. 55 °C)
- Expert initial operation (pressure test, flushing)

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

QUALITY MANAGEMENT

DRINKING WATER HYGIENE

3.2 Types of installation

3.2.1 Connection of drinking water tapping points

The quality of drinking water provided in an interior installation is entirely dependent on the observance of certain temperature ranges and the avoidance of stagnation. Traditional piping networks make it almost impossible to observe both requirements under the prevailing conditions of use. Therefore, drinking water tapping points are nowadays preferably interconnected in loop lines.

Interconnection of tapping points in a loop line proves to be an effective concept of avoiding stagnating water.

Examples of different installation types: T-installations can lead to water ेत stagnating in the lines. <u>* x</u> 載り A loop line avoids stagnation in a drinking water installation from the very beginning. X ΦŴ Serial lines only make sense, if the last consumer is a frequently used ¥•¥ sanitary device. ₽₽

This description is based on directives applicable in Germany and the European Union.

These are the important directives on the quality of water that is intended for consumption by humans:

- Germany: Drinking Water Ordinance (Trinkwasserverordnung TrinkwV2001)
- European Union: Directive on Drinking Water 98/83/EG

Traditional pipe installation, for example, T-systems or floor manifolds for drinking water installation in buildings, frequently causes hygienic problems because of stagnation or inadmissible heating up of cold water. However, if no other way of installation can be used, water contamination should be avoided by forced pipe flushing.

DRINKING WATER HYGIENE

3.2.2 Fittings for hygienic piping



To provide the required drinking water quality, POLOPLAST has developed a new double wall union, which allows the types of piping indicated before to be used.

Several tapping points can now be connected, while the hygienic requirements of, for example, hotels and hospitals are fulfilled. They ensure that the entire amount of water contained in the piping is replaced at regular intervals. This prevents stagnation.

QUALITY MANAGEMENT

38.

4.1 Standards and regulations

The following standards and guidelines are relevant for planning, design and operating drinking water installation systems in Germany and have to be observed.

4.1.1 Planning of drinking water installation systems

EnEV	German Energy Saving Regulation
DIN 1988	Technical Regulations on Drinking Water Installations
DIN EN 806	Technical Regulations on Drinking Water Installations
DIN 2000	Guidelines on the Requirements on Drinking Water, Planning, Laying, Operation and
	Maintenance of Supply Systems
DIN 4109	Sound Protection in Structural Engineering
DIN 4102	Fire Prevention
DVGW W 551	Technical Measures for the Reduction of Legionella Growth in Drinking Water Installations
VDI 6023	Hygiene-conscious planning, laying, operation and maintenance of drinking water plants
POLOPLAST	Technical Manual
DVS 2207	Welding of Thermoplastics
DVS 2208	Machinery and Appliances for Welding Thermoplastics

4.1.2 System-specific standards

DIN EN ISO 15874	Parts 1-7	Plastics piping systems for hot and cold water installations – Polypropylene (PP)
	Part 1	General information
	Part 2	Pipes
	Part 3	Fittings
	Part 5	Fitness for purpose of the system
	Part 7 / TS	Conformity Assessment
DIN 8077		Polypropylene Pipe Systems, Dimensions
DIN 8078		Polypropylene Pipe Systems
		General Quality Requirements, Testing
DIN EN ISO 21003	Parts 1-7	Multilayer Composite Pipe Systems for Hot and Cold Water
		Installations within Buildings

Hygiene

DVGW W 270	Growth of Microorganisms on Materials used in Drinking Water Installations -
	Tests and Assessment
KTW	Guideline of the Federal Environmental Agency on the Assessment of Organic Materials
	in Contact with Drinking Water

DIN standards are similar to ISO standards. The ISO standards are valid all over the world, while DIN standards only apply in Germany. ISO stands for the International Standardisation Organisation, which is an Association of Standards Organisations of more than 150 countries. Lately, no clear dividing line between standards seems to exist. For example, an ISO standard can be directly transferred to a DIN standard, or a German standard can be filed with the international committee as a pre-standard, which is why parallelisms exist between standards. DRINKING WATER HYGIENE

4.2 Terms used

4.2.1 Standard dimension ratio

SDR is an index in use for the classification of plastic pipes, which describes the ratio between a pipe's outer diameter and its wall thickness.

$$SDR = 2 \cdot S + 1$$
 $SDR \approx \frac{d_a}{s}$

S = pipe series number s = wall thickness da = outer diameter

4.2.2 Pipe series number S

The nominal pipe series number is a dimensionless index, which is used for the calculation of the wall thickness of pipes.

The following equation is used for the calculation of the pipe series number S:

$$S = \frac{SDR - 1}{2}$$

Example: POLO-ECOSAN Pipe SDR 6 = S 2.5

4.2.3 Nominal pressure (PN)

The abbreviation PN (nominal pressure) indicates a reference value that is representative for a pipe system. This reference value was used in the first plastic pipe standards (for example, DIN 8077 -1974/1989) and was based on a safety factor of 2.0. The maximum working pressure of 20 bar, 16 bar, 10 bar only refers to a service life of 50 years at a working temperature of 20 °C. However, the maximum working pressure is lower for higher temperatures.

This circumstance frequently leads to confusion.

For an exact pipe classification under various operating conditions, newer versions of the respective standards (DIN 8077 – 1999 or EN ISO 15874 – 2003) therefore only state the pipe series S or the diameter-wall thickness ratio SDR.

ASSEMBLY GUIDELINES

INITIAL OPERATION

4.3 Requirements on pipe systems

Standards on the various products (for PP-R: EN ISO 15874), as well as the most recent standard on multilayer pipes (DIN EN ISO 21003) have introduced the term "classification of operating conditions".

The requirements made on pipe systems over their operating time according to ISO 15874 have been defined for four classes of application and are indicated in Table 1.

An admissible working pressure of 4 bar, 6 bar, 8 bar or, respectively, 10 bar is valid for each of the different classes of application.

All systems that comply with the conditions as stated in Table 1 must be suitable for conveying cold water at 20 °C and an admissible working pressure of 10 bar over a period of 50 years.

Only water or treated water may be used as heat transmitter in heating systems.

4.3.1 Classification of operational conditions

Class of application according to DIN EN ISO 15874

Class of application	Design temperature T_D	Duration of operation ^a at T _D vears	T _{max} °C	Duration of operation at T _{max} year(s)	T _{max} °C	Duration of operation at T _{times} h	Typical field of application
1ª	60	49	80	1	95	100	Hot water supply (60 °C)
2 ^a	70	49	80	1	95	100	Hot water supply (70 °C)
4 ^b	20 Followe 40 Followe 60 Followed by (see	20 d by 25		2.5 followed by e next column)	100	100	Underfloor heating and low-temperature radiator connection
56	20 Followe 60 Followe 80 Followed by (see	25 d by 10		1 followed by e next column)	100	100	High-temperature radiator connection

Annotation: This international standard does not apply, if values that are higher than those stated in the table are taken as a basis for T_D , T_{max} and T_{times} .

^a Pursuant to national regulations either class 1 or class 2 may be selected.

 If more than one design temperature is obtained for a class of application, the respective operating periods should be added up (for example, the universe of temperatures for class 5 and a duration of 50 years consists of the following:

- 20 °C over 14 years, followed by

- 60 °C over 25 years, followed by

- $\,$ 80 °C over 10 years, followed by

- 90 °C over 1 years, followed by

- 100 °C over 100 h.)

Table 1

4.3.2 Table of working pressure is exposed

Temperature Operating time	ting time	POLO-E SD	COSAN R 6	POLO-E SDF		POLO-ECO SDF)SAN ML5 8 7.4	POLO-I SDF	JV ML5 ? 7.4		DSAN ML3 R 11
emp	erai				М	aximum woi	kina pressu	ire		<u> </u>	
н do	bar	psi	bar	psi	bar	psi	bar	psi	bar	psi	
	1	36.0	522	18.0	261	31.0	450	28.5	413	19.9	289
	5	33.8	490	16.9	245	29.1	422	26.8	389	19.3	280
20 °C	10	32.8	476	16.4	238	28.4	412	26.1	379	19.0	276
	25	31.8	461	16.0	232	27.4	397	25.2	366	18.6	270
	50	30.9	448	15.5	225	26.7	387	24.5	355	18.4	267
	1	30.6	444	15.3	222	26.4	383	24.2	351	17.2	250
	5	28.7	416	14.4	209	24.8	360	22.7	329	16.6	241
30 °C	10	27.7	402	13.9	202	24.1	350	22.1	321	16.4	238
	25	26.8	389	13.4	194	23.3	338	21.3	309	16.1	234
	50	26.1	379	13.1	190	22.6	328	20.7	300	15.8	229
	1	25.8	374	12.9	187	22.5	326	20.6	299	14.8	215
	5	24.2	351	12.1	176	21.0	305	19.2	279	14.3	207
40 °C	10	23.6	342	11.8	171	20.4	296	18.7	271	14.1	205
	25	22.6	328	11.3	164	19.7	286	18.0	261	13.8	200
	50	22.0	319	11.0	160	19.1	277	17.4	252	13.6	197
	1	22.0	319	11.0	160	19.0	276	17.4	252	12.6	183
	5	20.4	296	10.2	148	17.8	258	16.2	235	12.2	177
50 °C	10	19.7	286	9.9	144	17.2	250	15.7	228	12.0	174
	25	19.1	277	9.6	139	16.6	241	15.1	219	11.7	170
	50	18.5	268	9.3	135	16.1	234	14.7	213	11.5	167
	1	18.5	268	9.3	135	16.1	234	14.7	213	10.7	155
	5	17.2	250	8.6	125	14.9	216	13.6	197	10.3	149
60 °C	10	16.6	241	8.3	120	14.5	210	13.2	191	10.1	147
	25	15.9	231	8.0	116	13.9	202	12.7	184	9.9	144
	50	15.3	222	7.7	112	13.5	196	12.3	178	9.7	141
	1	15.6	226	7.8	113	13.5	196	12.3	178	9.0	131
	5	14.3	207	7.2	104	12.5	181	11.4	165	8.6	125
70 °C	10	14.0	203	7.0	102	12.1	176	11.1	161	8.5	123
	25	12.1	176	6.1	88	11.6	168	9.6	139	8.3	120
	50	10.2	148	5.1	74	11.2	162	8.1	117	8.1	117
	1	13.1	190	6.5	94	11.3	164	10.3	149	7.5	109
80 °C	5	11.5	167	5.7	83	10.4	151	9.1	132	7.2	104
00 0	10	9.6	139	4.8	70	10.1	147	7.7	112	7.0	102
	25	7.6	110	3.8	55	9.6	139	6.2	90	6.9	100
	1	9.2	133	4.6	67	8.6	125	7.3	106	5.6	81
95 °C	5	6.2	90	3.1	45	7.9	115	4.9	71	5.3	77
	10	5.2	75	2.6	38	7.6	110	4.2	61	5.2	75

Admissible working pressure values for domestic installations (medium: water according to the Drinking Water Ordinance TrinkwV 2001)

Long-term stress behaviour of POLOPLAST pipes with a safety factor of 1.25

Table 2

SYSTEM DESCRIPTION

TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

SYSTEM REQUIREMENTS

PLANNING AND DESIGN

SDR = Standard Dimension Ratio (diameter / wall thickness ratio)

This table enables you to select the suitable pipe for your application. You should know the requirements made on the system (temperature, pressure).

Example of how to select a pipe:

Field of application: cold water Temperature of the medium: 20 °C Maximum working pressure: 10 bar

Selection:

Step 1: select the applicable temperature range > 20 °C Step 2: select the required service life > 50 years Step 3: maximum working pressure within the system 10 bar > pressure according to the table > 15.5 bar > Selection: **POLO-ECOSAN pipe SDR 11**

Field of application: hot water Temperature of the medium: 70 °C Maximum working pressure: 10 bar

Selection:

Step 1: select the applicable temperature range > 70 °C

Step 2: select the required service life > 50 years

Step 3: maximum working pressure within the system 10 bar > pressure according to the table > 11.4 bar > Selection: **POLO-ECOSAN ML5 pipe SDR 7.4**

Suggestion: pipe for a maximum working pressure of 10 bar

- cold water 20 °C: POLO-ECOSAN SDR 11
- hot water 70 °C: POLO-ECOSAN ML5 SDR 7.4

4.3.3 Stress that a pipe system is exposed

When planning and laying pipes, you should always take into account the following interior and exterior stress factors that the pipe system may be exposed to:

Factors:

- Temperature (from the inside and the outside)
- Chemical stress
- Pressure (excess and negative)
- Extension (tensile and compression load)
- Exterior loads from underground laying, traffic and heavy structural components

4.4 Chemical resistance

Thanks to the special properties of its materials, the POLO-ECOSAN installation system features excellent chemical resistance.

Chemical resistance of the POLO-ECOSAN fittings with brass inserts cannot be put on a level with the resistance of those system elements that are only made of PP-R.

Metallic copper, manganese or cobalt deteriorate the thermal ageing resistance of PP-R, above all, if the plasticized materials come into contact with these metals. Please contact POLOPLAST, if the pipe system is likely to come into contact with chemicals and other aggressive media.

Inquiry regarding the chemical resistance of the POLO-ECOSAN pipe system

	Area of a	pplication:	
Firm			Flow medium
Contact person			
Street		°C	Service temperature
Postal code/Place		mbar	Service pressure
Telephone		h/d	Running time
Telefax			
Building Project			Environment
Street			
Place		°C	Ambient temperature
		mbar	Ambient pressure
	included	not included	Data Sheets
			flow medium
Place, date			environment
	Contact person Street Postal code/Place Telephone Telefax Building Project Street Place	Firm Contact person Street Postal code/Place Telephone Telefax Building Project Street Place Included Included	Contact person Street Postal code/Place Postal code/Place Telephone h/d Telefax Building Project Street Place °C mbar not included included included

Send inquiry to: POLOPLAST GmbH Kirnachstrasse 17 . 87640 Ebenhofen . Germany Tel. +49 (0) 8342 . 7006 . 0 Fax +49 (0) 8342 . 7006 . 66 info@poloplast.com . www.poloplast.com

4.5 **Disinfection**

4.5.1 Thermal disinfection

In proven cases of contamination, the disinfection of drinking water installations must only be carried out for a limited period of time. Prophylactic disinfection measures do not comply with the minimum quality requirements of the Drinking Water Ordinance. The disinfection of drinking water installations can only be successful, if all sources of contamination have been removed beforehand. The limit values for disinfectant concentration specified in the Drinking Water Ordinance represent maximum values, which were set in accordance with hygienic and toxicological standards. However, no conclusions should be drawn automatically from these values with regard to the resistance of product materials to the disinfectant agents. Only trained specialists may carry out the disinfection of drinking water installations. The disinfection measures must be recorded in writing.

Disinfection measures carried out incorrectly can damage the drinking water installation. A combined thermal-chemical disinfection procedure is not permitted.

The thermal disinfection of POLOPLAST pipe systems must be carried out as follows:

- The water heater and the entire circulation system must be heated to at least 70 °C.
- Open all draw-off points in succession or line by line.
- Hot water at a temperature of 70 °C must be allowed to run from all draw-off points for at least three minutes.
- Do not allow the temperature to drop during the disinfection process.
- Do not exceed the maximum temperature of 95 °C.
- Take suitable measures to eliminate the risk of scalding.

The total thermal disinfection time for drinking water installations must not exceed 150 hours per year. Longer disinfection times or excessive temperatures can reduce the service life of the drinking water installation and can damage the system.

It might be necessary to carry out thermal disinfection on a regular basis to stop the growth of legionellae. Legionellae are killed at temperatures higher than 55 °C.

	at 70 °C	3 min.
Killing times	at 60 °C	60–120 min.
	at 55 °C	180–240 min.

To provide sufficient disinfection it must be made sure that a temperature level of more than 70 °C is achieved within the entire system.

Provided this type of disinfection is applied on a regular basis and a constant temperature level of more than 65 °C is guaranteed, the PP-RCT is particularly suitable, because of its improved long-term thermal resistance.

4.5.2 Chemical disinfection – "Shock disinfection"

During the process of chemical disinfection ("shock disinfection") in accordance with Pt. 7.5.2 of the ÖNORM-Standard B 5019, the disinfecting agent can be fed into the cold water circulation or the warm water circulation, respectively. When the disinfecting agent is fed into the warm water circulation, the temperature must first be reduced to below 25 °C. Carrying out "shock disinfections" at higher temperatures is not permissible, as premature material damage cannot be ruled out. In relation to the service life of the installed system, the number of disinfecting procedures must not exceed 5 cycles. No drinking water may be drawn either during the disinfection process or during the subsequent flushing of the system with cold water.

Table 3 lists the concentration and contact times of chemicals on the basis of ÖNORM-Standard B 5019.

Active component	Chemical formula	Max. concentration applied	Contact time	Max. water temp. in the system
Chlorine Dioxide	CIO ₂	6 mg/l as ClO ₂	8 to 12 hrs	< 25 °C
Hypochlorite	CIO-	50 mg/l as Cl _{2 (chlorine)}	8 to 12 hrs	< 25 °C
Permanganate	MnO ₄ -	15 mg/l	24 hrs	< 25 °C
Hydrogen Peroxide	H ₂ O ₂	150 mg/l	24 hrs	< 25 °C

 Table 3: Concentration and contact times of chemicals for chemical disinfection

During the application the applied concentration and application temperature may not be exceeded at any point within the pipe system.

4.5.3 Continuous metered addition of chemicals - "Permanent disinfection"

The continuous metered addition of chemicals according to Pt. 9 of the ÖNORM-Standard B 5019 is only permissible in instances when repeated decontamination processes (thermal, chemical, according to Section 7 of the ÖNORM-Standard) did not produce the desired results and where the systems in question have low levels of biofilm.

It must be stated that the continuous metered addition of chemicals can in no way replace the structural refurbishment of the pipe system and should be regarded merely as temporary supporting measure until such a time as the refurbishment takes place, and not as prophylactic measure against Legionella.

If the timeframe and the maximum water temperature are exceeded, damage to the component parts of the pipe systems (pipe, seals, o-rings, etc.) cannot be ruled out. This applies to all prevalent materials used in plumbing technology (types of metal, plastics and elastomers).

Table 4 lists the concentration and contact times of chemicals on the basis of ÖNORM-Standard B 5019.

Table 4

Table 3

Active component	Chemical formula	Max. concentration applied	Max. period of application	Max. water temp. in the system
Chlorine Dioxide**	CIO ₂	0.4 mg/l as CIO ₂	4 months	0° C
Hypochlorite	CIO-	0.3 mg/l as Cl _{2 (chlorine)}	4 months	60 °C
Chlorine	Cl ₂	0.3 mg/l as Cl _{2 (chlorine)}	4 months	60 °C
Chlorine Dioxide**	CIO ₂	0.4 mg/l as ClO ₂	18 months	< 25 °C
Hypochlorite	CIO-	0.3 mg/l as Cl _{2 (chlorine)}	18 months	< 25 °C
Chlorine	Cl ₂	0.3 mg/l as Cl _{2 (chlorine)}	18 months	< 25 °C

Table 4: Concentration and contact times of chemicals for continuous metered addition

^{**} For the disinfection process using chlorine dioxide (listed as CIO_2) the maximum amount that can be added into the pipe system is 0.4 mg/l CIO_2 .

SYSTEM DESCRIPTION

5.1 Dimensioning of drinking water systems

5.1.1 Differentiating calculation procedure

Planning and construction of drinking water installations are based the DIN EN 806 standard or relevant national collateral standards such as DIN 1988-300. These define the procedure used to determine the pipe diameters, which is achieved by calculating the loss of pressure in the pipe system. The pressure loss depends on the pipe length, pipe material, the type of fittings used, as well as the flow rate, which is influenced by the number and size of taps and fittings.

The following data is required to determine pressure losses and pipe diameters:

- supply pressure or outlet pressure after a pressure-reducing valve or pressure increase
- difference in geodetic altitude
- pressure loss related to fittings (e.g., water meters, filters, water softening equipment, etc.)
- minimum flow pressure at the tapping points
- loss of pressure due to the resistance of the pipe materials used
- coefficients of losses relating to fittings and connecting elements used

Below, we introduce a simplified calculation (acc. to EN 806) and a differentiating calculation procedure (acc. to DIN 1988) for the determination of the pipe diameters. The choice of alternative methods allows the selection of the most suitable method for the relevant application. The simplified calculation is recommended for small-scale projects and simple drinking water installations. However, in the interest of hygiene, the differentiating calculation procedure is preferable, in order to ensure the precise calculation and dimensioning of the installation.

The model for the differentiating calculation is illustrated in the process depicted below.

Determine total flow rates and allocate to relevant sections Starting from the farthest tapping point and leading to the supply line, the calculated flow rates are added, and the total flow rates are allocated to the corresponding line sections.								
Determine peak flow rate from the total flow rate To calculate the pipeline system, all draw-off tapping points are generally assigned to their respective calculated flows. Simultaneous water tapping depends on the type of use (e.g. residential or communal systems). Generally, it can be assumed that not all taps will be opened at the same time. For piping installations in residential buildings, the corresponding peak flow rate can be determined using the formula / diagram in DIN 1988 Section 300.								
Determine pressure difference for pipe resistance and individual	resistance values.							
Differentiating Calculation Procedure	Simplified Calculation Procedure							
Differentiating Calculation Procedure Determine pressure loss value from individual resistance values via loss correction values	Simplified Calculation Procedure Calculate total pressure loss from pipe resistance of all segments and compare to available pressure difference							
Determine pressure loss value from individual resistance values via	Calculate total pressure loss from pipe resistance of all segments and							

. 47

For sound insulation reasons and in order to limit pressure surges, the calculated flow rate must not exceed the values provided below.

Maximum flow rate in accordance with DIN 1988-300

Table 5

	Line section	Maximum calculated flow rate for a duration of			
		≤ 15 min	> 15 min		
connecting lines		2 m/s	2 m/s		
Supply pipes	pipe sections with pipe valve fittings featuring low pressure loss ($\zeta <$ 2.5) *	5 m/s	2 m/s		
	pipe sections with pipe valve fittings with higher loss coefficient values **	2.5 m/s	2 m/s		

* e.g. piston slide valves acc. to DIN 3500, ball valves, slanted seat valves acc. to DIN 3502 (starting from DN 20)

** e.g. shut-off valves acc. to DIN 351

5.1.2 Minimum flow pressures of tapping points

Standard minimum flow pressure values and calculated flow rates for selected drinking water tapping points $$_{\mbox{Table 6}}$$

	Type of drinking water tapping point		Calc	ulated flow for out	let of
			mixed	water*	either cold or hot drinking water
Minimum flow pressure _{Pmin} bar			volume flow cold I/s	volume flow hot I/s	volume flow I/s
0.5	outlet valves without aerator**	DN 15	-	_	0.30
0.5		DN 20	-	—	0.50
0.5		DN 25	_	_	1.00
1.0	outlet valves with aerator	DN 10	_	_	0.15
1.0		DN 15	_	_	0.15
1.0	shower heads for cleaning showers		0.10	0.10	0.20
1.2	pressure flusher according to DIN 3265. part 1	DN 15	_	_	0.70
1.2	pressure flusher according to DIN 3265. part 1	DN 20	_	_	1.00
0.4	pressure flusher according to DIN 3265. part 1	DN 25	_	_	1.00
1.0	pressure flusher for urinals	DN 15	_	_	0.30
1.0	household dishwasher	DN 15	_	_	0.15
1.0	household washing machine	DN 15	_	_	0.25
1.0	mixers for showers	DN 15	0.15	0.15	-
1.0	mixers for bath tubs	DN 15	0.15	0.15	-
1.0	mixers for kitchen sinks	DN 15	0.07	0.07	-
1.0	mixers for wash basins	DN 15	0.07	0.07	-
1.0	mixers for bidets	DN 15	0.07	0.07	_
1.0	mixer	DN 20	0.30	0.30	-
0.5	cistern according to DIN 19542	DN 15	_	_	0.13
1.0	electric water boiler	DN 15	_	_	0.10***

The calculated flow rates for the supply of mixed water are based on a temperature of 15 °C for cold water and 60 °C for heated drinking water.
 For outlet valves without aerator and with threaded hose connection, the pressure loss in the hose assembly (up to a length of 10 m) and in the connected appliance (e.g. lawn sprinkler) is taken into account as a flat rate minimum flow pressure. In this case, the minimum flow pressure increases by 1.0 bar to 1.5 bar.

*** with fully opened throttle valve.

Annotation: When determining the pipe diameter, draw-off points which are not included in the table as well as valves and fittings of a similar kind with flow rates of fittings or minimum flow pressures that are greater than indicated must be taken into account as per the recommendations of the manufacturer.

DRINKING WATER HYGIENE

5.1.3 Peak flow rate according to DIN 1988

Simultaneous water tapping depends on the type of use (e.g. in residential buildings, hotels, etc.). Generally, it can be assumed that not all connected taps will be fully open at the same time. Consequently, the cumulative flow can be converted into the peak flow rate.

Determination of the peak flow rate $V_{\rm S}$ from the total flow rate $\Sigma V_{\rm R}$






Table 7:

Values in I/s for residential buildings, offices / administration buildings with an assumed calculated flow rate of the tapping point $V_{\rm R}$ < 0.5 I/s Table 7

$\Sigma V_{\rm R}$	Vs	$\Sigma V_{\rm R}$	Vs	$\Sigma V_{\rm R}$	Vs	ΣV_{R}	Vs	$\Sigma V_{\rm R}$	Vs	ΣV_{B}	Vs	$\Sigma V_{\rm R}$	Vs	$\Sigma V_{\rm R}$	Vs
).02	0.02	1.02	0.55	2.02	0.80	3.02	0.98	4.02	1.14	5.10	1.28	10.10	1.79	15.10	2.17
.02	0.02	1.02	0.55	2.02	0.80	3.02	0.98	4.02	1.14	5.20	1.29	10.10	1.80	15.20	2.17
.04 .06	0.04	1.04	0.55	2.04	0.80	3.04	0.98	4.04	1.14	5.30	1.29	10.20	1.80	15.20	2.10
.08	0.08	1.08	0.57	2.08	0.81	3.08	0.99	4.08	1.14	5.40	1.32	10.40	1.82	15.40	2.19
.10	0.10	1.10	0.57	2.10	0.81	3.10	0.99	4.10	1.15	5.50	1.33	10.50	1.82	15.50	2.20
.12	0.12	1.12	0.58	2.12	0.82	3.12	1.00	4.12	1.15	5.60	1.34	10.60	1.83	15.60	2.21
).14	0.14	1.14	0.58	2.14	0.82	3.14	1.00	4.14	1.15	5.70	1.35	10.70	1.84	15.70	2.21
0.16	0.16	1.16	0.59	2.16	0.82	3.16	1.00	4.16	1.16	5.80	1.36	10.80	1.85	15.80	2.22
).18	0.18	1.18	0.59	2.18	0.83	3.18	1.01	4.18	1.16	5.90	1.38	10.90	1.86	15.90	2.23
0.20	0.19	1.20	0.60	2.20	0.83	3.20	1.01	4.20	1.16	6.00	1.39	11.00	1.87	16.00	2.23
).22	0.21	1.22	0.61	2.22	0.84	3.22	1.01	4.22	1.16	6.10	1.40	11.10	1.87	16.10	2.24
).24	0.22	1.24	0.61	2.24	0.84	3.24	1.02	4.24	1.17	6.20	1.41	11.20	1.88	16.20	2.25
0.26	0.23	1.26	0.62	2.26	0.84	3.26	1.02	4.26	1.17	6.30	1.42	11.30	1.89	16.30	2.25
0.28	0.24	1.28	0.62	2.28	0.85	3.28	1.02	4.28	1.17	6.40	1.43	11.40	1.90	16.40	2.26
).30	0.26	1.30	0.63	2.30	0.85	3.30	1.03	4.30	1.17	6.50	1.44	11.50	1.91	16.50	2.27
).32	0.27	1.32	0.63	2.32	0.86	3.32	1.03	4.32	1.18	6.60	1.45	11.60	1.91	16.60	2.27
0.34	0.28	1.34	0.64	2.34	0.86	3.34	1.03	4.34	1.18	6.70	1.47	11.70	1.92	16.70	2.28
0.36	0.29	1.36	0.64	2.36	0.86	3.36	1.04	4.36	1.18	6.80	1.48	11.80	1.93	16.80	2.29
0.38	0.30	1.38	0.65	2.38	0.87	3.38	1.04	4.38	1.19	6.90	1.49	11.90	1.94	16.90	2.29
0.40	0.31	1.40	0.65	2.40	0.87	3.40	1.04	4.40	1.19	7.00	1.50	12.00	1.95	17.00	2.30
0.42	0.32	1.42	0.66	2.42	0.88	3.42	1.05	4.42	1.19	7.10	1.51	12.10	1.95	17.10	2.31
0.44	0.33	1.44	0.66	2.44	0.88	3.44	1.05	4.44	1.19	7.20	1.52	12.20	1.96	17.20	2.31
0.46	0.34	1.46	0.67	2.46	0.88	3.46	1.05	4.46	1.20	7.30	1.53	12.30	1.97	17.30	2.32
0.48	0.35	1.48	0.67	2.48	0.89	3.48	1.06	4.48	1.20	7.40	1.54	12.40	1.98	17.40	2.33
).50	0.36	1.50	0.68	2.50	0.89	3.50	1.06	4.50	1.20	7.50	1.55	12.50	1.99	17.50	2.33
).50).52	0.37	1.52	0.68	2.52	0.89	3.52	1.06	4.52	1.20	7.60	1.56	12.60	1.99	17.60	2.34
).52	0.38	1.54	0.69	2.52	0.00	3.54	1.00	4.54	1.20	7.70	1.57	12.00	2.00	17.70	2.34
0.54 0.56	0.30	1.54	0.69	2.54	0.90	3.56	1.00	4.54	1.21	7.80	1.58	12.70	2.00	17.80	2.35
0.50 0.58	0.39	1.58	0.09	2.58	0.90	3.58	1.07	4.58	1.21	7.90	1.59	12.00	2.01	17.90	2.35
0.60	0.40	1.60	0.70	2.60	0.91	3.60	1.07	4.60	1.22	8.00	1.60	13.00	2.02	18.00	2.36
0.62	0.41	1.62	0.71	2.62	0.91	3.62	1.08	4.62	1.22	8.10	1.61	13.10	2.03	18.10	2.37
0.64	0.42	1.64	0.71	2.64	0.92	3.64	1.08	4.64	1.22	8.20	1.62	13.20	2.04	18.20	2.38
0.66	0.43	1.66	0.72	2.66	0.92	3.66	1.08	4.66	1.22	8.30	1.63	13.30	2.05	18.30	2.38
0.68	0.43	1.68	0.72	2.68	0.92	3.68	1.09	4.68	1.23	8.40	1.64	13.40	2.05	18.40	2.39
0.70	0.44	1.70	0.73	2.70	0.93	3.70	1.09	4.70	1.23	8.50	1.65	13.50	2.06	18.50	2.40
0.72	0.45	1.72	0.73	2.72	0.93	3.72	1.09	4.72	1.23	8.60	1.66	13.60	2.07	18.60	2.40
0.74	0.46	1.74	0.74	2.74	0.93	3.74	1.09	4.74	1.23	8.70	1.67	13.70	2.07	18.70	2.41
0.76	0.46	1.76	0.74	2.76	0.94	3.76	1.10	4.76	1.24	8.80	1.67	13.80	2.08	18.80	2.41
0.78	0.47	1.78	0.74	2.78	0.94	3.78	1.10	4.78	1.24	8.90	1.68	13.90	2.09	18.90	2.42
0.80	0.48	1.80	0.75	2.80	0.94	3.80	1.10	4.80	1.24	9.00	1.69	14.00	2.10	19.00	2.43
0.82	0.48	1.82	0.75	2.82	0.95	3.82	1.11	4.82	1.24	9.10	1.70	14.10	2.10	19.10	2.43
0.84	0.49	1.84	0.76	2.84	0.95	3.84	1.11	4.84	1.25	9.20	1.71	14.20	2.11	19.20	2.44
0.86	0.50	1.86	0.76	2.86	0.95	3.86	1.11	4.86	1.25	9.30	1.72	14.30	2.12	19.30	2.44
0.88	0.50	1.88	0.77	2.88	0.96	3.88	1.12	4.88	1.25	9.40	1.73	14.40	2.12	19.40	2.45
0.90	0.51	1.90	0.77	2.90	0.96	3.90	1.12	4.90	1.25	9.50	1.74	14.50	2.13	19.50	2.46
0.92	0.52	1.92	0.77	2.92	0.96	3.92	1.12	4.92	1.26	9.60	1.75	14.60	2.14	19.60	2.46
0.94	0.52	1.94	0.78	2.94	0.97	3.94	1.12	4.94	1.26	9.70	1.76	14.70	2.15	19.70	2.47
0.96	0.53	1.96	0.78	2.96	0.97	3.96	1.13	4.96	1.26	9.80	1.76	14.80	2.15	19.80	2.47
	0.54	1.98	0.79	2.98	0.97	3.98	1.13	4.98	1.26	9.90	1.77	14.90	2.16	19.90	2.48
0.98															

TRANSPORTATION AND STORAGE

SYSTEM DESCRIPTION

5.1.4 Single resistance values ζ

			D · · · · · · · ·
Fitting Individual resistance	Graphic symbol	Remark	Resistance coefficient value ζ
Тее	<u> </u>	branching, dividing flow	1.3
	<u> </u>	passage for dividing flow	0.3
	rt	counter current for dividing flow	1.4
	×+	branching, merging flow	1.3
	v <u>→</u> →	passage for merging flow	2.5
	<u>⊻</u> +	counter current for merging flow	3.0
Elbow 90°	t t		1.2
Elbow 45°	t		0.7
Socket	\Rightarrow		0.25
Reducer		by 1 dimension	0.4
		by 2 dimensions	0.6
	, ,	by 3 dimensions	0.7
		more than 4 dimensions	0.9
Wall union	vt F		1.7
Double wall union	<i>י</i> ∕\\\ ^C		1.5
Short cross over	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~		1.9
Transition with internal thread			0.5
Transition with internal thread, reduced	— m →		0.8
Transition with external thread	— → m		0.4
Transition with external thread, reduced			0.8
Transition elbow with thread			1.7
Tee with transition, dividing flow			1.6
Slanted seat valve			3.0
Slanted seat valve with back-flow prevention			3.8
Shut-off valve	>		7.0
Ball valve	Þ¤\$		0.4

5.1.5 Pressure loss tables

Pressure loss due to pipe resistance R and flow rate v depending on flow V

Roughness: 0.007 mm

Pipe SDR 6

Temperature 20 °C

Density: 998.29 kg/m³ Kin. viscosity: 1.004E-06 m²/s

		Dimension	16 mm	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm
		Wall thickness	2.7 mm	3.4 mm	4.2 mm	5.4 mm	6.7 mm	8.3 mm	10.5 mm	12.5 mm	15.0 mm	18.3 mm	20.8 mm
l/s	m³/h												
0.01	0.04	R in mbar/m	0.41	0.15	0.05	0.02	0.01						
		v in m/s	0.11	0.07	0.05	0.03	0.02						
0.02	0.07	R	1.24	0.45	0.16	0.05	0.02	0.01					
0.00		V	0.23	0.15	0.09	0.06	0.04	0.02					
0.03	0.11	R	2.41	0.87	0.30	0.10	0.03	0.01					
0.04	0.14	v R	0.34 3.89	0.22	0.14 0.48	0.08	0.05	0.03	0.01				
0.04	0.14	v	0.45	0.29	0.18	0.13	0.03	0.02	0.03				
0.05	0.18	R	5.66	2.02	0.69	0.22	0.08	0.03	0.01				
		v	0.57	0.37	0.23	0.14	0.09	0.06	0.04				
0.06	0.22	R	7.70	2.74	0.94	0.30	0.10	0.04	0.01	0.01			
0.07	0.05	V	0.68	0.44	0.28	0.17	0.11	0.07	0.04	0.03			
0.07	0.25	R v	10.02 0.79	3.55 0.51	1.21 0.32	0.39 0.20	0.13 0.13	0.05 0.08	0.02 0.05	0.01 0.04			
0.08	0.29	R	12.59	4.46	1.51	0.20	0.13	0.06	0.03	0.04			
0.00	0.20	v	0.91	0.58	0.37	0.23	0.14	0.09	0.06	0.04			
0.09	0.32	R	15.43	5.45	1.85	0.59	0.20	0.07	0.02	0.01			
		v	1.02	0.66	0.42	0.25	0.16	0.10	0.06	0.05			
0.10	0.36	R	18.52	6.52	2.21	0.70	0.24	0.08	0.03	0.01	0.01		
0.10	0.40	V	1.13	0.73	0.46	0.28	0.18	0.11	0.07	0.05	0.04		
0.12	0.43	R v	25.44 1.36	8.92 0.88	3.01 0.55	0.95 0.34	0.33 0.22	0.11 0.14	0.04 0.09	0.02 0.06	0.01 0.04		
0.14	0.50	R	33.33	11.66	3.92	1.23	0.22	0.14	0.05	0.00	0.04		
0.14	0.00	v	1.59	1.02	0.65	0.40	0.25	0.16	0.10	0.02	0.05		
0.16	0.58	R	42.17	14.71	4.93	1.55	0.53	0.18	0.06	0.03	0.01		
		v	1.81	1.17	0.74	0.45	0.29	0.18	0.12	0.08	0.06		
0.18	0.65	R	51.96	18.07	6.05	1.89	0.65	0.22	0.08	0.03	0.01	0.01	
0.00	0.70	V	2.04	1.32	0.83	0.51	0.32	0.21	0.13	0.09	0.06	0.04	
0.20	0.72	R v	62.68 2.27	21.75 1.46	7.26 0.92	2.27 0.57	0.78 0.36	0.27 0.23	0.09 0.14	0.04 0.10	0.02 0.07	0.01 0.05	
0.30	1.08	R	129.98	44.65	14.77	4.58	1.56	0.23	0.14	0.08	0.07	0.03	0.01
0.00	1.00	v	3.40	2.19	1.39	0.85	0.54	0.34	0.22	0.15	0.11	0.07	0.05
0.40	1.44	R	219.69	74.89	24.60	7.58	2.56	0.87	0.29	0.13	0.05	0.02	0.01
		v	4.53	2.92	1.85	1.13	0.72	0.46	0.29	0.20	0.14	0.09	0.07
0.50	1.80	R	331.49	112.32	36.68	11.24	3.78	1.28	0.43	0.19	0.08	0.03	0.02
0.00	0.10	V	5.67	3.65	2.31	1.42	0.90	0.57	0.36	0.25	0.18	0.12	0.09
0.60	2.16	R	465.18	156.82	50.97	15.55	5.21	1.76	0.59	0.26	0.11	0.04	0.02
0.70	2.52	v R	6.80 620.65	4.38 208.34	2.77 67.43	1.70 20.49	1.08 6.85	0.68	0.43	0.31	0.21	0.14	0.11
0.70	2.02	v	7.93	5.12	3.23	1.98	1.26	0.80	0.51	0.34	0.25	0.03	0.03
0.80	2.88	R	797.84	266.84	86.05	26.05	8.68	2.91	0.97	0.42	0.18	0.07	0.04
		v	9.07	5.85	3.70	2.27	1.44	0.91	0.58	0.41	0.28	0.19	0.15
0.90	3.24	R	996.69	332.29	106.80	32.22	10.72	3.58	1.20	0.52	0.22	0.08	0.05
1.00	0.00	V	10.20	6.58	4.16	2.55	1.62	1.03	0.65	0.46	0.32	0.21	0.16
1.00	3.60	R		404.65 7.31	129.67 4.62	39.01	12.94	4.32	1.44	0.63 0.51	0.26	0.10 0.24	0.06 0.18
1.10	3.96	v R		483.92	4.62	2.83 46.40	1.80 15.36	1.14 5.11	0.72	0.51	0.35	0.24	0.18
	0.00	v		8.04	5.08	3.12	1.98	1.26	0.79	0.74	0.31	0.12	0.07
1.20	4.32	R		570.09	181.75	54.40	17.97	5.97	1.98	0.86	0.36	0.14	0.08
		v		8.77	5.54	3.40	2.16	1.37	0.87	0.61	0.42	0.28	0.22
1.30	4.68	R		663.13	210.95	62.99	20.77	6.89	2.29	0.99	0.42	0.16	0.09
1.40	E 0.4	V		9.50	6.01	3.68	2.34	1.48	0.94	0.66	0.46	0.31	0.24
1.40	5.04	R		763.06	242.24	72.18	23.75	7.86	2.61	1.13	0.47	0.18	0.10
1.60	5.76	v R		10.23	6.47 311.09	3.97 92.33	2.52 30.28	1.60	1.01 3.31	0.71 1.43	0.50	0.33	0.26
1.00	5.70	n V			7.39	4.53	2.88	1.83	1.15	0.81	0.00	0.23	0.12
1.80	6.48	R			388.29	114.85	37.56	12.37	4.08	1.76	0.74	0.28	0.15
		V			8.32	5.10	3.24	2.05	1.30	0.92	0.64	0.43	0.33
2.00	7.20	R			473.81	139.72	45.56	14.97	4.93	2.13	0.89	0.34	0.18
		V			9.24	5.67	3.60	2.28	1.44	1.02	0.71	0.47	0.37
2.20	7.92	R			567.64	166.93	54.30	17.80	5.85	2.52	1.05	0.40	0.22
	8.64	v R			10.17	6.23 196.48	3.96	2.51	1.59	1.12 2.94	0.78	0.52	0.40
2.40						19h 48	63.77	20.85	6.84	294	122	114/	11.25

ASSEMBLY GUIDELINES

INITIAL OPERATION

bb mVh v			Dimension	16 mm	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm
2.00 9.30 8.8 8.9 9.20 7.30 2.84 7.90 2.80 7.34 2.80 7.35 2.84 7.35 2.85 7.35 2.85 7.35 2.85 7.35 2.85 7.35 2.85 7.35 2.85 7.35 7	1/0	m3/h	Wall thickness	2.7 mm	3.4 mm	4.2 mm	5.4 mm	6.7 mm	8.3 mm	10.5 mm	12.5 mm	15.0 mm	18.3 mm	20.8 mm
b b b 7.37 4.68 2.07 1.88 1.22 0.02 0.64 0.64 0.64 0.64 0.64 0.64 0.64 0.64 0.64 0.64 0.64 0.65 0.33 3.00 1.08 R 2001 1.08 0.24 1.03 0.24 1.03 0.24 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.23 1.03 0.03 0.23 1.03 1.24 0.03 0.05 0.23 1.03 1.04 0.03 0.05 0.23 1.03 1.04 0.03 0.05 0.03 0.05			R				228.36	73.96	24.14	7.90	3.40	1.41	0.54	0.29
v v v v z							7.37	4.68	2.97	1.88	1.32	0.92	0.61	0.48
3.00 10.80 R P <	2.80	10.08												
b b	3.00	10.80												
1 - 0 $1 - 0$ <			v				8.50							0.55
4.00 14.40 R 1 516.57 175.64 53.41 17.31 7.39 3.05 1.15 0.06 5.00 16.00 R 2006.00 66.50 21.44 9.16 3.75 1.42 0.77 5.00 18.00 R 2006.00 66.50 21.44 9.16 3.75 1.75 0.60 5.50 19.80 S.4 P 2006.00 6.36 3.37 2.30 1.53 1.15 0.62 5.50 19.80 R 2006.00 6.38 3.37 2.30 1.54 1.16 1.16 1.17 0.85 1.33 1.10 1.17 1.16 1.17 1.18 1.16 1.1	3.50	12.60												
	4.00	14.40												
Image: Constraint of the section of the sec			v					7.20	4.57	2.89	2.04	1.41	0.95	0.73
18.0018.0018.0018.0018.0011.00 <th< td=""><td>4.50</td><td>16.20</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></th<>	4.50	16.20												
550 1980 R N <td>5.00</td> <td>18.00</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>1</td> <td></td> <td></td> <td></td> <td></td> <td></td>	5.00	18.00							1					
0vv000.283.972.801.951.301.016.002160RV367.871.3990.57.71.55.16.362.221.221.121.006.854.333.061.777.365.271.421.105.0022.00RV1.7477.365.248.433.068.433.068.433.061.541.651.297.5027.00RV1.7477.365.448.2429.573.574.671.462.271.378.0028.00RV1.66.86.573.574.072.681.891.468.513.00R1.29.41.711.375.443.222.681.891.468.543.503.60R2.281.381.991.462.272.801.891.468.543.574.072.281.384.092.881.834.092.881.831.659.503.574.572.281.381.653.581.653.581.771.653.582.861.831.651.659.503.574.572.281.381.651.653.581.781.651.651.651.651.651.651.651.651.651.651.651.651.651.651.651.651.651.651.65	5.50	10.00							1					
6.00 21.60 8 8 13.90 36.57 113.90 36.57 15.51 6.56 2.33 3.06 2.22 1.42 1.10 6.50 23.40 R 12.56 44.73 3.06 2.22 1.42 1.10 7.00 25.20 R 15.249 44.73 20.61 43.31 2.30 1.55 1.42 1.45 1.28 7.00 R 15.249 44.73 20.61 43.31 2.36 1.38 1.465 1.28 8.00 28.60 R 106.43 62.57 26.39 1.07 4.33 1.20 4.38 1.46 1.28 1.46 1.28 1.46 1.28 1.46 1.28 1.46 1.28 1.46 1.28 1.46 1.28 1.40 4.39 2.27 1.39 3.37 2.48 1.39 3.37 2.48 1.39 3.37 2.48 1.39 3.37 2.48 1.39 2.43 1.37 2.48 1.39 2.42 2.48 1.39 2.43 2.43 1.55 1.49	5.50	19.80												
65.0 23.40 R <thr< <="" td=""><td>6.00</td><td>21.60</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></thr<>	6.00	21.60												
v v	0.50	00.40						10.80						
7.00 25.20 R <	6.50	23.40												
7.50 27.00 R N<	7.00	25.20												
vvkkk <th< td=""><td>7.50</td><td>07.00</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></th<>	7.50	07.00												
8.00 28.00 R V Alot Pields G257 G239 10.77 4.03 217 8.00 30.00 R V Pields 22043 7011 2945 12.04 4.50 2.243 189 1.268 1.38 2.10 2.10 1.50 9.00 32.40 R V Pields 6.50 4.58 1.38 4.99 2.56 9.00 34.20 R V Pields 6.50 4.58 1.38 2.13 1.66 9.00 36.00 R V Pields 7.72 5.00 4.56 3.56 1.71 10.00 36.00 R Pields Pields 7.72 5.00 3.64 2.86 1.35 11.00 39.60 R Pields Pields 1.420 4.224 9.40 2.01 3.89 2.60 2.01 1.343 4.24 4.44 2.44 2.44 2.44 2.44 2.44 2.44 2.44 2.44 2.44 2.44 2.44 2.45 2.55	7.50	27.00												
8.50 30.60 R<	8.00	28.80												
vvvii <th< td=""><td>0.50</td><td>00.00</td><td>-</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></th<>	0.50	00.00	-											
9.00 32.40 R<	8.50	30.60												
9.50 34.20 R<	9.00	32.40												
v v v v i	0.50	0.4.00							10.27					
10.00 36.00 R 9 9 22 40.00 16.26 6.05 3.25 10.50 37.80 R 72.2 5.09 3.84 2.38 1.83 10.00 39.60 R 77.28 5.35 3.71 2.48 1.33 11.00 39.60 R 114.03 47.82 18.40 7.21 3.37 11.50 41.40 R 12.00 43.20 R 2.60 2.01 12.00 43.20 R 134.49 5.31 2.24 8.46 4.53 12.00 43.00 R 184.59 5.31 2.24 8.46 4.53 12.00 45.00 R 165.61 65.47 2.42 2.95 2.29 13.00 46.80 R 166.81 65.47 2.48 9.92 2.38 16.03 3.74 2.29 5.25 13.00 46.80 R 166.1 65.47 2.48 <td>9.50</td> <td>34.20</td> <td></td>	9.50	34.20												
10.50 37.80 R v 10.42 43.82 17.80 6.62 3.55 11.00 39.60 R v 7.84 5.53 3.71 2.48 132 11.50 41.40 R 2.01 7.84 5.60 3.89 2.60 2.01 11.50 41.40 R v 124.06 5.188 2.107 7.83 4.19 12.00 43.20 R v 134.49 66.31 9.22 2.81 8.46 4.53 12.50 45.00 R 9.02 6.637 4.22 2.84 2.20 13.00 46.80 R 9.02 6.37 4.22 2.84 2.86 13.50 48.60 R v 156.61 65.47 28.48 9.81 5.25 14.00 50.40 R v 180.37 75.30 30.41 11.52 6.61 14.00 50.40 R v 180.37 75.30 30.41 11.25 6.61 14.50 52.20 R	10.00	36.00												
vvooo7.885.583.712.481.9211.0039.60Rv11.407.945.603.892.602.0111.5041.40Rv124.0651.9821.077.834.1912.0043.20Rv12.065.864.072.722.1112.0043.20Rv134.4956.3122.818.464.5313.0045.80R145.3460.8024.619.124.8813.0046.80R19.026.574.422.292.2913.0046.80R156.6165.4726.488.815.2513.0046.80R19.25.864.013.0111.255.6114.0050.40R180.377.5303.0111.255.6614.0050.40R180.377.5303.0111.256.6114.0050.40R180.377.5303.0111.256.6114.0050.40R180.377.5303.0411.256.6315.0054.00R19.218.637.7345.863.133.4414.0050.40R19.219.06.6312.4418.6317.733.9814.0057.60R19.219.06.6412.786.6313.4412.7815.0057.60R19.2 <td< td=""><td>10.50</td><td>07.00</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></td<>	10.50	07.00												
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	10.50	37.00												
11.50 41.40 R	11.00	39.60								114.03				3.87
vvoss <th< td=""><td>11.50</td><td>41.40</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></th<>	11.50	41.40												
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	11.50	41.40												
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	12.00	43.20	R							134.49	56.31		8.46	4.53
vvvv902 6.37 4.42 2.95 2.29 13.0046.80RV156.61 65.47 26.48 9.31 5.25 13.5048.60RV9.38 6.62 4.60 3.07 2.38 13.5048.60RV180.37 75.30 28.41 10.52 5.62 9.74 6.88 4.77 3.19 2.47 6.62 9.74 6.88 4.77 3.19 14.00 50.40 RV10.11 7.13 4.95 3.31 2.66 14.50 52.20 RV10.11 7.13 4.95 3.31 2.65 15.00 54.00 RV10.11 7.13 4.95 3.31 2.65 15.00 57.60 RV10.11 7.13 4.95 3.34 2.65 16.00 57.60 RV10.14 7.38 5.66 3.78 2.75 17.00 61.20 RV10.14 7.94 9.697 3.006 1.441 7.69 9.00 64.80 RV10.14 7.94 9.66 3.76 3.78 2.33 17.00 61.20 RV10.14 7.94 9.66 9.677 3.906 1.441 7.69 9.00 64.80 RV10.157 4.25 3.78 2.75 3.78 2.93 17.00 61.20 RIIII	12.50	45.00												
vvo9.386.624.603.072.3813.00 $\frac{8}{20}$ $\frac{8}{20}$ $\frac{8}{20}$ $\frac{8}{20}$ $\frac{8}{20}$ $\frac{10}{20}$ $\frac{5}{20}$ 14.00 50.40 R v 10.11 10.11 7.530 30.41 11.25 6.01 14.00 $\frac{5}{22.00}$ R v 10.11 7.13 4.95 3.14 2.56 14.50 52.20 R v 10.11 7.13 4.95 3.431 2.56 15.00 54.00 R v 10.11 7.38 51.3 34.34 2.65 15.00 57.60 R V 10.11 7.38 51.3 34.34 2.65 16.00 57.60 R $I1.25$ 6.61 7.88 7.530 30.64 14.41 7.69 17.00 61.20 R $I1.25$ $I1.630$ $I1.63$ $I1.63$ $I1.630$ $I1.63$ $I1.63$ $I1.63$ 18.00 64.80 R V $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ 19.00 64.80 R V $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ 20.00 72.00 R $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ 21.00 75.00 R $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ $I1.63$ 22.00 72.00 R $I1.63$ I	12.00	40.00												
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	13.00	46.80												
vvv009.746.884.773.192.4714.00 50.40 Rv180.3775.3030.4111.256.0114.50 52.20 Rv10.117.134.953.312.5614.50 52.20 Rv6.884.773.982.6515.00 54.00 Rv6.883.46112.786.83 75.00 76.00 R7.60R7.663.782.9316.00 57.60 R8.863.663.782.9317.00 61.20 R8.863.782.9318.0064.80R8.866.614.023.1118.0064.80R8.8616.138.60 9.00 R9.873.9412.1348.7617.9419.0068.40R9.973.9614.573.5621.0075.60R9.966.724.493.8621.0075.60R9.686.724.493.8621.0075.60R9.686.724.933.8621.0075.60R9.749.6610.197.074.3822.0079.20R9.686.724.933.8422.0079.20R9.686.724.933.8422.0079.20R9.75.428.3915.833.54424.0086.40<	13 50	48.60												
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$													3.19	2.47
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	14.00	50.40												
vvoo7.385.133.432.6515.0054.00R V 85.0034.6112.786.8316.0057.60R V 96.9739.0614.417.6916.0057.60R V 96.9739.0614.417.6917.0061.20R V 108.8043.7816.138.6018.0064.80R V 108.8043.7816.138.6019.0068.40R V 101.809.176.374.253.2919.0068.40R V 101.97.749.5610.579.0072.00R V V V V 101.97.744.9621.0075.60R V V V V V 10.197.7528.3922.0079.20R V V V V V 10.197.75428.3915.0823.0082.80R V V V V V 15.083.843.8422.0079.20R V V V V V V V 15.0824.0086.40R V V V V V V V 15.0825.0090.00R V V V V V V V 16.3325.0090.00R V V V V V <	14 50	52 20								10.11				
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	1 1100		v								7.38			
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	15.00	54.00												
v v e 8.15 5.66 3.78 2.93 17.00 61.20 R V 108.80 43.78 16.13 8.60 18.00 V V 108.80 8.66 6.01 4.02 3.11 18.00 R V I I 121.31 48.76 17.94 9.56 9.017 6.37 4.25 3.29 9.07 6.37 4.25 3.29 19.00 68.40 R V I 134.47 54.00 19.85 10.57 9.017 72.00 R V I I 148.31 59.49 21.84 11.63 20.00 72.00 R V I <tdi< td=""><td>16.00</td><td>57.60</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tdi<>	16.00	57.60												
v v a			v								8.15	5.66	3.78	2.93
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	17.00	61.20												
v v i v i <	18.00	64.80												
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$			v								9.17	6.37	4.25	3.29
20.00 72.00 R v 148.31 59.49 21.84 11.63 21.00 75.60 R v 10.19 7.07 4.73 3.66 21.00 75.60 R v 10.19 7.07 4.73 3.66 22.00 79.20 R v 10.19 7.43 4.96 3.84 22.00 79.20 R v 11.63 7.43 4.96 3.84 22.00 79.20 R v 10.19 7.78 5.20 4.03 23.00 82.80 R v 11.63 10.19 7.754 28.39 15.08 24.00 86.40 R v 11.63 8.49 5.67 4.39 25.00 90.00 R 10.19 10.19 7.753 28.39 15.03 25.00 90.00 R 10.19 10.19 90.87 33.21 17.63	19.00	68.40												
v v 10.19 7.07 4.73 3.66 21.00 75.60 R 65.25 23.93 12.73 v v - 65.25 23.93 12.73 22.00 79.20 R - - - 74.3 4.96 3.84 22.00 79.20 R v - - - 74.3 4.96 3.84 23.00 82.80 R v - - - - 7.78 5.20 4.03 24.00 86.40 R - - - - 84.08 30.75 16.33 25.00 90.00 R - - - - - - 4.39	20.00	72.00												
v v 7.43 4.96 3.84 22.00 79.20 R 71.27 26.12 13.88 v v - - 77.26 5.20 4.03 23.00 82.80 R - - - 77.54 28.39 15.08 24.00 86.40 v - - 84.08 30.75 16.33 25.00 90.00 R - - - 90.87 33.21 17.63	01.00	75.00									10.19			
22.00 79.20 R v 26.12 13.88 23.00 82.80 R - - - 77.54 52.00 4.03 23.00 82.80 R - - - - 77.54 28.39 15.08 24.00 86.40 V - - - 84.08 30.75 16.33 25.00 90.00 R - - - 90.87 33.21 17.63	21.00	/5.60												
23.00 82.80 R v 15.08 v v 81.3 5.44 4.21 24.00 86.40 R 84.08 30.75 16.33 v v 25.00 90.00 R 90.87 33.21 17.63	22.00	79.20										71.27	26.12	13.88
v R State State </td <td>00.00</td> <td>00.00</td> <td></td>	00.00	00.00												
24.00 86.40 R N 16.33 v N N N N 16.33 4.39 25.00 90.00 R N N N 17.63	23.00	82.80												
25.00 90.00 R 90.87 33.21 17.63	24.00	86.40										84.08	30.75	16.33
	25.00	00.00												
	25.00	90.00	K V									90.87 8.84	33.21	17.63 4.58

SYSTEM DESCRIPTION

Pressure loss due to pipe resistance R and flow rate v depending on flow V

Pipes SDR 7,4

Temperature 20 °C

Roughness: 0.007 mm Density: 998.29 kg/m³ Kin. viscosity: 1.004E-06 m²/s

		Dimension	16 mm	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm	160 mm	200 mm	250 mm
		Wall thickness	2.2 mm	2.8 mm	3.5 mm	4.4 mm	5.5 mm	6.9 mm	8.6 mm	10.3 mm	12.3 mm	15.1 mm	17.1 mm	21.6 mm	27.4 mm	34.2 mm
l/s	m³/h															
0.01	0.04	R in mbar/m	0.27	0.10	0.04	0.01										
0.02	0.07	v in m/s R	0.09	0.06	0.04	0.02	0.01									
0.02	0.07	V	0.02	0.00	0.08	0.05	0.03									
0.03	0.11	R	1.58	0.58	0.21	0.06	0.02									
0.04	0.14	v R	0.28 2.55	0.18	0.12	0.07	0.05	0.01								
		v	0.38	0.25	0.16	0.09	0.06	0.04								
0.05	0.18	R v	3.70 0.47	1.34 0.31	0.47 0.20	0.15 0.12	0.05 0.08	0.02 0.05								
0.06	0.22	R	5.03	1.82	0.20	0.12	0.00	0.03	0.01							
0.07	0.05	V	0.57	0.37	0.24	0.14	0.09	0.06	0.04							
0.07	0.25	R v	6.54 0.66	2.36 0.43	0.83 0.28	0.25 0.17	0.09 0.11	0.03 0.07	0.01 0.04							
0.08	0.29	R	8.21	2.96	1.04	0.32	0.11	0.04	0.01							
0.00	0.32	V	0.76	0.49	0.31	0.19	0.12	0.08	0.05							
0.09	0.32	R v	10.05 0.85	3.61 0.55	1.26 0.35	0.38 0.21	0.14 0.14	0.05 0.09	0.02							
0.10	0.36	R	12.05	4.32	1.51	0.46	0.16	0.06	0.02	0.01						
0.12	0.43	v R	0.95 16.52	0.61 5.90	0.39	0.24	0.15	0.10	0.06	0.04						
0.12	0.43	V	1.14	0.74	0.47	0.02	0.22	0.00	0.03	0.01						
0.14	0.50	R	21.62	7.70	2.67	0.81	0.28	0.10	0.03	0.02						
0.16	0.58	v R	1.32 27.33	0.86	0.55	0.33	0.21	0.14	0.08	0.06						
		V	1.51	0.98	0.63	0.38	0.24	0.16	0.10	0.07						
0.18	0.65	R v	33.63 1.70	11.91 1.11	4.11 0.71	1.24 0.43	0.43 0.27	0.15 0.17	0.05 0.11	0.02 0.08	0.01 0.05					
0.20	0.72	R	40.52	14.32	4.94	1.48	0.27	0.17	0.06	0.00	0.03					
0.00	1.00	V	1.89	1.23	0.79	0.47	0.30	0.19	0.12	0.09	0.06	0.01				
0.30	1.08	R v	83.68 2.84	29.30 1.84	10.01 1.18	2.98 0.71	1.03 0.45	0.36 0.29	0.12 0.18	0.05 0.13	0.02 0.09	0.01 0.06				
0.40	1.44	R	140.98	49.02	16.64	4.92	1.70	0.59	0.20	0.09	0.04	0.01	0.01			
0.50	1.80	v R	3.78 212.17	2.46 73.35	1.57 24.77	0.95 7.29	0.61 2.50	0.39	0.24	0.17	0.12	0.08	0.06			
0.00	1.00	v	4.73	3.07	1.96	1.18	0.76	0.49	0.23	0.13	0.03	0.02	0.01			
0.60	2.16	R	297.12	102.21	34.36	10.06	3.45	1.20	0.39	0.17	0.07	0.03	0.02			
0.70	2.52	v R	5.68 395.72	3.68 135.57	2.36 45.40	1.42 13.24	0.91 4.52	0.58 1.57	0.36	0.26	0.18	0.12	0.09	0.01		
0.1.0	2.02	v	6.62	4.30	2.75	1.66	1.06	0.68	0.42	0.30	0.21	0.14	0.11	0.07		
0.80	2.88	R	507.93	173.38	57.86	16.82	5.73	1.98	0.64	0.28	0.12	0.05	0.03 0.12	0.01 0.07		
0.90	3.24	v R	7.57 633.70	4.91 215.63	3.14 71.73	1.89 20.78	1.21 7.06	0.78 2.43	0.49	0.34	0.24	0.16	0.12	0.07		
		v	8.52	5.53	3.54	2.13	1.36	0.87	0.55	0.39	0.27	0.18	0.14	0.08		
1.00	3.60	R v	773.00 9.46	262.30 6.14	87.00 3.93	25.14 2.37	8.52 1.51	2.93 0.97	0.95 0.61	0.42 0.43	0.17 0.30	0.07 0.20	0.04 0.15	0.01 0.09		
1.10	3.96	R	925.81	313.36	103.67	29.87	10.11	3.47	1.12	0.49	0.00	0.08	0.04	0.03		
1.00	4.00	V	10.41	6.75	4.32	2.60	1.67	1.07	0.67	0.47	0.33	0.22	0.17	0.10	0.01	
1.20	4.32	R v		368.81 7.37	121.73 4.72	34.99 2.84	11.82 1.82	4.05 1.17	1.31 0.73	0.58 0.52	0.24 0.36	0.09 0.24	0.05 0.19	0.02	0.01 0.07	
1.30	4.68	R		428.65	141.17	40.48	13.65	4.67	1.51	0.66	0.28	0.11	0.06	0.02	0.01	
1.40	5.04	v R		7.98 492.86	5.11 162.00	3.08 46.35	1.97 15.60	1.26 5.33	0.79	0.56	0.39	0.26	0.20	0.12	0.08	
1.40	0.04	v		8.60	5.50	3.31	2.12	1.36	0.85	0.60	0.42	0.28	0.07	0.13	0.01	
1.60	5.76	R		634.39	207.77	59.21	19.86	6.77	2.18	0.96	0.40	0.15	0.08	0.03	0.01	
1.80	6.48	v R		9.82 793.36	6.29 259.03	3.78 73.57	2.42 24.61	1.55 8.37	0.97	0.69	0.48	0.32	0.25	0.15	0.10	
		v		11.05	7.07	4.26	2.73	1.75	1.09	0.77	0.54	0.36	0.28	0.17	0.11	
2.00	7.20	R			315.77	89.40	29.83	10.12	3.24	1.42	0.59	0.23	0.12	0.04	0.01	
2.20	7.92	v R			7.86 377.96	4.73 106.70	3.03 35.52	1.94 12.02	1.21 3.85	0.86	0.60	0.40	0.31	0.19	0.12	0.01
		v			8.65	5.20	3.33	2.14	1.34	0.95	0.65	0.44	0.34	0.21	0.13	0.08
2.40	8.64	R v			445.60 9.43	125.47 5.68	41.67 3.63	14.08 2.33	4.50 1.46	1.96 1.03	0.81 0.71	0.31 0.48	0.17 0.37	0.05 0.22	0.02 0.14	0.01 0.09
2.60	9.36	R			518.69	145.71	48.30	16.29	5.19	2.26	0.93	0.48	0.37	0.22	0.14	0.09
		V			10.22	6.15	3.94	2.53	1.58	1.12	0.77	0.52	0.40	0.24	0.16	0.10

ASSEMBLY GUIDELINES

INITIAL OPERATION

		Dimension	16 mm	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm	160 mm	200 mm	250 mm
		Wall thickness	2.2 mm	2.8 mm	3.5 mm	4.4 mm	5.5 mm	6.9 mm	8.6 mm	10.3 mm	12.3 mm	15.1 mm	17.1 mm	21.6 mm	27.4 mm	34.2 mm
l/s	m³/h															
2.80	10.08	R v				167.40 6.62	55.38 4.24	18.64 2.72	5.93 1.70	2.58 1.20	1.06 0.83	0.41 0.56	0.22 0.43	0.07 0.26	0.02	0.01 0.11
3.00	10.80	R				190.56	62.93	21.15	6.72	2.92	1.20	0.46	0.25	0.08	0.03	0.01
3.50	12.60	v R				7.10 254.82	4.54 83.82	2.91 28.07	1.82 8.89	1.29 3.86	0.89	0.60	0.46	0.28	0.18	0.12
		v				8.28	5.30	3.40	2.12	1.51	1.04	0.70	0.54	0.33	0.21	0.14
4.00	14.40	R v				328.14 9.46	107.58 6.06	35.90 3.89	11.33 2.43	4.91 1.72	2.01 1.19	0.77 0.80	0.42 0.62	0.12 0.37	0.04 0.24	0.02 0.15
4.50	16.20	R				410.53	134.19	44.65	14.06	6.07	2.49	0.95	0.51	0.15	0.05	0.02
5.00	18.00	v R				10.65	6.81 163.65	4.37 54.32	2.73 17.05	1.94 7.36	1.34 3.01	0.90	0.69	0.42	0.27	0.17
		V					7.57	4.86	3.03	2.15	1.49	1.00	0.77	0.47	0.30	0.19
5.50	19.80	R v					195.95 8.33	64.88 5.34	20.32 3.34	8.75 2.37	3.57 1.64	1.36 1.10	0.73 0.85	0.22 0.51	0.08	0.03 0.21
6.00	21.60	R					231.09	76.36	23.86	10.26	4.18	1.60	0.86	0.26	0.09	0.03
6.50	23.40	v R					9.08 269.06	5.83 88.73	3.64 27.68	2.58 11.89	1.79 4.84	1.20 1.84	0.93	0.56	0.36	0.23
7.00	05.00	V					9.84	6.32	3.95	2.80	1.93	1.30	1.00	0.61	0.39	0.25
7.00	25.20	R v					309.86 10.60	102.00 6.80	31.76 4.25	13.62 3.01	5.54 2.08	2.11 1.40	1.13 1.08	0.34 0.65	0.12 0.42	0.04 0.27
7.50	27.00	R						116.17	36.10 4.55	15.47	6.28	2.39	1.28	0.38 0.70	0.13	0.05
8.00	28.80	V R						7.29 131.24	40.72	3.23 17.42	2.23 7.07	1.50 2.68	1.16 1.44	0.43	0.45	0.29
0.50	30.60	v R						7.77	4.86	3.44	2.38 7.90	1.60 3.00	1.24 1.60	0.75	0.48	0.31
8.50	30.00	R V						8.26	45.60 5.16	19.49 3.66	2.53	3.00	1.60	0.48 0.79	0.17 0.51	0.06 0.33
9.00	32.40	R						164.05 8.74	50.75 5.46	21.67 3.87	8.77 2.68	3.32 1.80	1.78 1.39	0.53 0.84	0.18 0.54	0.06 0.35
9.50	34.20	v R						181.80	56.16	23.96	9.69	3.67	1.96	0.84	0.34	0.35
10.00	36.00	v R						9.23 200.45	5.77 61.84	4.09 26.35	2.83 10.65	1.90 4.03	1.47 2.15	0.89	0.57	0.37
10.00	30.00	V						9.72	6.07	4.30	2.98	2.00	1.54	0.04	0.22	0.08
10.50	37.80	R v						219.98 10.20	67.78 6.37	28.86 4.52	11.65 3.13	4.40 2.10	2.35 1.62	0.69 0.98	0.24 0.63	0.08 0.41
11.00	39.60	R						10.20	73.99	31.48	12.70	4.79	2.56	0.36	0.03	0.09
11.50	41.40	v R							6.68 80.46	4.73 34.20	3.27 13.78	2.20 5.20	1.70 2.77	1.03 0.82	0.66	0.42
		v							6.98	4.95	3.42	2.30	1.78	1.07	0.69	0.44
12.00	43.20	R v							87.20 7.28	37.04 5.16	14.91 3.57	5.62 2.40	3.00 1.85	0.88 1.12	0.31 0.72	0.11 0.46
12.50	45.00	R							94.20	39.98	16.09	6.06	3.23	0.95	0.33	0.11
13.00	46.80	v R							7.59	5.38 43.03	3.72 17.30	2.50 6.51	1.93 3.47	1.17 1.02	0.75	0.48
		v							7.89	5.59	3.87	2.60	2.01	1.21	0.79	0.50
13.50	48.60	R v							108.99 8.19	46.19 5.81	18.56 4.02	6.98 2.70	3.71 2.08	1.09 1.26	0.38	0.13 0.52
14.00	50.40	R							116.78	49.46	19.86	7.46	3.97	1.17	0.41	0.14
14.50	52.20	v R							8.50 124.83	6.02 52.84	4.17 21.20	2.80 7.96	2.16 4.23	1.31 1.24	0.85	0.54 0.15
45.00	54.00	V							8.80	6.24	4.32	2.90	2.24	1.35	0.88	0.56
15.00	54.00	R v							133.14 9.10	56.33 6.45	22.59 4.47	8.48 3.00	4.50 2.32	1.32 1.40	0.46 0.91	0.16 0.58
16.00	57.60	R							150.56	63.62 6.88	25.48 4.76	9.55	5.07 2.47	1.49 1.49	0.52	0.18 0.62
17.00	61.20	v R							9.71 169.03	71.35	28.54	3.20 10.69	5.67	1.49	0.97	0.02
18.00	64.80	v R							10.32	7.31 79.51	5.06 31.77	3.40 11.88	2.63 6.30	1.59 1.84	1.03	0.66
10.00	04.00	V N								7.74	5.36	3.60	2.78	1.68	1.09	0.22
19.00	68.40	R v								88.09 8.17	35.16 5.66	13.14 3.80	6.96 2.93	2.03 1.77	0.71 1.15	0.24 0.73
20.00	72.00	R								97.11	38.73	14.45	7.65	2.23	0.78	0.26
21.00	75.60	v R								8.60 106.56	5.95 42.46	4.00	3.09 8.38	1.87 2.44	1.21 0.85	0.77
		v								9.04	6.25	4.20	3.24	1.96	1.27	0.81
22.00	79.20	R v								116.44 9.47	46.35 6.55	17.26 4.40	9.13 3.40	2.66 2.05	0.92	0.31 0.85
23.00	82.80	R								126.75	50.41	18.76	9.92	2.89	1.00	0.34
24.00	86.40	v R								9.90 137.49	6.85 54.64	4.60	3.55 10.73	2.15 3.12	1.39	0.89
		v								10.33	7.14	4.80	3.71	2.24	1.45	0.93
25.00	90.00	R v									59.03 7.44	21.93 5.00	11.58 3.86	3.36 2.33	1.17 1.51	0.39 0.97
26.00	93.60	R									63.59	23.60	12.46	3.62	1.25	0.42
		V									7.74	5.20	4.02	2.43	1.57	1.00

SYSTEM DESCRIPTION

DRINKING WATER HYGIENE

		Dimension Wall thickness														
l/s	m³/h	Wan anoknoso	2.2 11111	2.0 mm	0.0 mm	4.4 mm	0.0 mm	0.5 mm	0.0 1111	10.0 1111	12.0 mm	10.1 1111	17.1 1111	21.0 mm	27.4 000	04.2 mi
27.00	97.20	R									68.31	25.34	13.37	3.88	1.34	0.45
		v									8.04	5.40	4.17	2.52	1.63	1.04
28.00	100.80	R v									73.20 8.34	27.13 5.60	14.31 4.32	4.15 2.61	1.43 1.69	0.48
29.00	104.40	R									78.26	28.98	15.28	4.42	1.53	0.52
30.00	108.00	v R									8.63 83.48	5.80 30.90	4.48 16.28	2.71 4.71	1.75 1.63	1.12 0.55
30.00	100.00	v N									8.93	6.00	4.63	2.80	1.81	1.16
32.00	115.20	R									94.42	34.90	18.37	5.31	1.83	0.62
34.00	122.40	v R									9.53 106.01	6.40 39.14	4.94 20.59	2.99 5.94	1.93 2.05	1.24
	100.00	V									10.12	6.80	5.25	3.17	2.05	1.3
36.00	129.60	R v										43.61 7.20	22.93 5.56	6.60 3.36	2.27 2.17	0.70
38.00	136.80	R										48.32	25.38	7.30	2.51	0.84
40.00	144.00	v R										7.60 53.27	5.87 27.96	3.55 8.03	2.29 2.76	1.4
		v										8.00	6.18	3.73	2.42	1.54
42.00	151.20	R v										58.45 8.40	30.67 6.49	8.80 3.92	3.02 2.54	1.0 ⁻ 1.6
44.00	158.40	R										63.87	33.49	9.60	3.29	1.10
46.00	105.00	V										8.80	6.80	4.11	2.66	1.70
46.00	165.60	R v										69.53 9.20	36.43 7.10	10.43 4.29	3.57 2.78	1.20 1.78
48.00	172.80	R										75.42	39.50	11.30	3.86	1.29
50.00	180.00	v R										9.60 81.54	7.41 42.68	4.48 12.19	2.90 4.17	1.8
		v										10.00	7.72	4.67	3.02	1.93
52.00	187.20	R v											45.99 8.03	13.13 4.85	4.48 3.14	1.50 2.0 ⁻
54.00	194.40	R											49.41	14.09	4.81	1.6
56.00	201.60	v R											8.34 52.96	5.04 15.09	3.26 5.15	2.08
30.00	201.00	V N											8.65	5.23	3.38	2.16
58.00	208.80	R											56.63	16.12	5.49	1.83
60.00	216.00	v R											8.96 60.41	5.41 17.18	3.50 5.85	2.24
		v											9.27	5.60	3.62	2.3
62.00	223.20	R v											64.32 9.57	18.28 5.79	6.22 3.74	2.0
64.00	230.40	R											68.35	19.41	6.60	2.20
66.00	237.60	v R											9.88 72.50	5.97 20.57	3.87 6.99	2.4
00.00	201.00	v											10.19	6.16	3.99	2.5
68.00	244.80	R v												21.77 6.35	7.39 4.11	2.40 2.63
70.00	252.00	R												22.99	7.81	2.6
70.00	050.00	V												6.53	4.23	2.70
72.00	259.20	R v												24.26 6.72	8.23 4.35	2.73
74.00	266.40	R												25.55	8.66	2.8
78.00	280.80	v R												6.91 28.24	4.47 9.56	2.8
		v												7.28	4.71	3.0
80.00	288.00	R v												29.63 7.47	10.03 4.83	3.3 3.0
82.00	295.20	R												31.05	10.51	3.4
84.00	202.40	V												7.65	4.95	3.1
84.00	302.40	R V												32.51 7.84	11.00 5.07	3.64 3.24
86.00	309.60	R												34.00	11.49	3.8
88.00	316.80	v R												8.03 35.52	5.19 12.00	3.3
		v												8.21	5.31	3.40
90.00	324.00	R v												37.08 8.40	12.52 5.44	4.14 3.4

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

Pressure loss due to pipe resistance R and flow rate v depending on flow V

Pipes SDR 11

Temperatur 20 °C	Roughness: 0.007 mm	Density: 998.29 kg/m ³	Kin. viscosity: 1.004E-06 m ² /s

		Dimension	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm	160 mm	200 mm	250 mm
		Wall thickness	1.9 mm	2.3 mm	2.9 mm	3.7 mm	4.6 mm	5.8 mm	6.8 mm	8.2 mm	10.0 mm	11.4 mm	14.6 mm	18.2 mm	22.7 mm
l/s	m³/h														
0.01	0.04	R in mbar/m v in m/s	0.06 0.05	0.02 0.03	0.01 0.02										
0.02	0.07	R v	0.18 0.10	0.06 0.06	0.02	0.01 0.02									
0.03	0.11	R v	0.34 0.15	0.12 0.09	0.04 0.06	0.01 0.04									
0.04	0.14	R v	0.54 0.19	0.18 0.12	0.06 0.07	0.02 0.05	0.01 0.03								
0.05	0.18	R	0.78	0.27 0.15	0.08	0.03	0.01 0.04								
0.06	0.22	R v	1.05 0.29	0.36 0.18	0.11 0.11	0.04 0.07	0.01 0.05	0.01 0.03							
0.07	0.25	R	1.36 0.34	0.46 0.21	0.14 0.13	0.05	0.02	0.01 0.03							
0.08	0.29	R	1.70 0.39	0.58	0.18	0.06	0.02	0.01 0.04							
0.09	0.32	R	2.07 0.44	0.70	0.22	0.08	0.03	0.01							
0.10	0.36	R	2.48 0.49	0.84	0.26	0.09	0.03	0.01	0.01 0.03						
0.12	0.43	R	3.38 0.58	0.31 1.14 0.37	0.35	0.12	0.03	0.02 0.06	0.01 0.04						
0.14	0.50	R	4.40	1.48	0.46	0.16	0.06	0.02	0.01						
0.16	0.58	R R	0.68	0.43	0.26	0.17	0.11	0.07	0.05						
0.18	0.65	R	0.78	0.49	0.30	0.19	0.12	0.08	0.05	0.01					
0.20	0.72	R	0.87	0.55	0.33	0.22	0.14	0.09	0.06	0.04					
0.30	1.08	R R	0.97 16.61	0.61 5.50	0.37 1.67	0.24 0.59	0.15 0.21	0.10	0.07	0.05	0.01				
0.40	1.44	R R	1.46 27.68	0.92 9.11	0.56 2.75	0.36 0.97	0.23	0.14	0.10 0.05	0.07	0.05				
0.50	1.80	R R	1.94 41.30	1.22 13.53	0.74 4.07	0.48	0.31	0.19	0.14	0.09	0.06	0.01			
0.60	2.16	R R	2.43 57.42	1.53 18.73	0.93	0.60	0.38	0.24	0.17	0.12	0.08	0.06			
0.70	2.52	R	2.91 75.99	1.84 24.69	1.11 7.37	0.72 2.58	0.46	0.29	0.20	0.14	0.09	0.07			
0.80	2.88	v R	3.40 97.01	2.14 31.41	1.30 9.34	0.84	0.54	0.34	0.24 0.16	0.16	0.11 0.03	0.09			
0.90	3.24	v R	3.88 120.44	2.45 38.87	1.48 11.53	0.96	0.61 1.37	0.39	0.27	0.19	0.13	0.10	0.01		
1.00	3.60	v R	4.37 146.28	2.75 47.08	1.67 13.93	1.08 4.85	0.69	0.43	0.30	0.21	0.14	0.11 0.02	0.07		
1.10	3.96	v R	4.85 174.52	3.06 56.03	1.85 16.53	1.20 5.74	0.76	0.48	0.34	0.24	0.16	0.12	0.07		
1.20	4.32	v R	5.34 205.14	3.37 65.70	2.04 19.34	1.32 6.71	0.84	0.53	0.37	0.26	0.17	0.13	0.08		
1.30	4.68	v R	5.82 238.15	3.67 76.11	2.23 22.36	1.44 7.74	0.92	0.58	0.41	0.28	0.19	0.15 0.03	0.09		
1.40	5.04	v R	6.31 273.54	3.98 87.24	2.41 25.57	1.56 8.84	0.99	0.63	0.44	0.31	0.20	0.16	0.10		
1.60	5.76	v R	6.79 351.43	4.28	2.60	1.68	1.07	0.67	0.47	0.33	0.22	0.17	0.10		
1.80	6.48	R R	7.76	4.90	2.97	1.92	1.22 4.69	0.77	0.54	0.23	0.03	0.00	0.12	0.01	
		v	8.73	5.51	3.34	2.16	1.38	0.87	0.61	0.42	0.28	0.22	0.13	0.09	
2.00	7.20	R V	535.58 9.70	169.14 6.12	49.09 3.71	16.84 2.40	5.67 1.53	1.86 0.96	0.79	0.33	0.13 0.31	0.07	0.02	0.01	
2.20	7.92	R v	641.81 10.67	202.17 6.73	58.51 4.08	20.03	6.73 1.68	2.21	0.94	0.39	0.15	0.08	0.03	0.01	
2.40	8.64	R v		238.06 7.34	68.72 4.45	23.48 2.88	7.87 1.84	2.58 1.16	1.10 0.81	0.46 0.56	0.18 0.38	0.10 0.29	0.03	0.01	
2.60	9.36	R v		276.78 7.95	79.71 4.82	27.18 3.11	9.10 1.99	2.97 1.25	1.26 0.88	0.53 0.61	0.20 0.41	0.11 0.32	0.03 0.19	0.01 0.12	

		Dimension	20 mm			40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm	160 mm	200 mm	250 mm
.,		Wall thickness	1.9 mm	2.3 mm	2.9 mm	3.7 mm	4.6 mm	5.8 mm	6.8 mm	8.2 mm	10.0 mm	11.4 mm	14.6 mm	18.2 mm	22.7 mm
1/s 2.80	m³/h 10.08	R		318.35	91.49	31.14	10.40	3.40	1.44	0.60	0.23	0.13	0.04	0.01	
2.00	10.00	n V		8.57	5.19	3.35	2.14	1.35	0.95	0.66	0.23	0.13	0.04	0.01	
3.00	10.80	R		362.76	104.04	35.35	11.79	3.84	1.63	0.68	0.26	0.14	0.04	0.02	0.01
3.50	12.60	v R		9.18 486.16	5.56 138.82	3.59 47.00	2.29 15.62	1.45 5.07	1.01 2.15	0.71	0.47	0.37	0.22	0.14	0.09
		v		10.71	6.49	4.19	2.68	1.69	1.18	0.82	0.55	0.43	0.26	0.17	0.11
4.00	14.40	R v			178.44 7.42	60.21 4.79	19.95 3.06	6.46 1.93	2.73 1.35	1.14 0.94	0.43 0.63	0.24 0.49	0.07 0.30	0.03 0.19	0.01 0.12
4.50	16.20	R			222.89	74.99	24.77	8.01	3.38	1.41	0.53	0.29	0.09	0.03	0.01
5.00	18.00	v R			8.35 272.15	5.39 91.32	3.44 30.09	2.17 9.70	1.52 4.08	1.06 1.70	0.71	0.55	0.33	0.21	0.14
5.00	10.00	V			9.27	5.99	3.82	2.41	1.69	1.18	0.04	0.61	0.37	0.04	0.01
5.50	19.80	R v			326.21 10.20	109.21 6.59	35.90 4.21	11.55 2.65	4.85 1.86	2.02 1.29	0.76 0.86	0.41 0.67	0.13 0.41	0.04 0.26	0.02 0.17
6.00	21.60	R			10.20	128.65	42.20	13.55	5.69	2.36	0.89	0.48	0.41	0.20	0.02
0.50	00.40	V				7.19	4.59	2.89	2.03	1.41	0.94	0.73	0.45	0.29	0.18
6.50	23.40	R v				149.64 7.79	48.99 4.97	15.70 3.13	6.58 2.20	2.73 1.53	1.03 1.02	0.56 0.79	0.17 0.48	0.06 0.31	0.02
7.00	25.20	R				172.17	56.26	17.99	7.53	3.12	1.18	0.64	0.20	0.07	0.02
7.50	27.00	v R				8.39 196.24	5.35 64.02	3.37 20.44	2.36 8.55	1.65 3.53	1.10 1.33	0.85	0.52	0.33	0.21
		v				8.99	5.74	3.61	2.53	1.76	1.18	0.91	0.56	0.36	0.23
8.00	28.80	R v				221.85 9.58	72.27 6.12	23.03 3.86	9.62 2.70	3.97 1.88	1.50 1.26	0.81 0.98	0.25 0.60	0.08 0.38	0.03
8.50	30.60	R				249.01	80.99	25.78	10.76	4.44	1.67	0.90	0.28	0.09	0.24
9.00	32.40	v R				10.18	6.50	4.10	2.87	2.00 4.93	1.34 1.85	1.04	0.63	0.40	0.26
9.00	32.40	n V					90.20 6.88	28.67 4.34	11.95 3.04	2.12	1.41	1.00 1.10	0.51	0.10 0.43	0.04
9.50	34.20	R					99.89	31.70	13.20	5.44	2.04	1.10	0.34	0.11	0.04
10.00	36.00	v R					7.27	4.58 34.89	3.21 14.52	2.23 5.97	1.49 2.24	1.16 1.21	0.71	0.45	0.29
		V					7.65	4.82	3.38	2.35	1.57	1.22	0.74	0.48	0.30
10.50	37.80	R v					120.71 8.03	38.22 5.06	15.89 3.55	6.53 2.47	2.45 1.65	1.32 1.28	0.40 0.78	0.14 0.50	0.05 0.32
11.00	39.60	R					131.84	41.69	17.32	7.12	2.67	1.44	0.44	0.15	0.05
11.50	41.40	v R					8.41 143.45	5.30 45.32	3.72 18.81	2.59 7.72	1.73 2.89	1.34 1.56	0.82	0.52	0.33
	41.40	v v					8.80	5.54	3.88	2.70	1.81	1.40	0.47	0.55	0.35
12.00	43.20	R					155.54 9.18	49.08	20.36	8.35	3.13 1.89	1.69	0.51	0.17	0.06
12.50	45.00	v R					168.11	5.78 53.00	4.05 21.96	2.82 9.00	3.37	1.46 1.82	0.89 0.55	0.57 0.19	0.36
10.00	40.00	V					9.56	6.02	4.22	2.94	1.96	1.52	0.93	0.59	0.38
13.00	46.80	R v					181.16 9.94	57.06 6.27	23.63 4.39	9.68 3.06	3.62 2.04	1.95 1.58	0.59 0.97	0.20 0.62	0.07 0.40
13.50	48.60	R					194.69	61.26	25.35	10.38	3.88	2.09	0.63	0.22	0.07
14.00	50.40	v R					10.33	6.51 65.61	4.56 27.13	3.17 11.10	2.12 4.14	1.65 2.23	1.00 0.68	0.64	0.41
		V						6.75	4.73	3.29	2.20	1.71	1.04	0.67	0.43
14.50	52.20	R v						70.10 6.99	28.97 4.90	11.84 3.41	4.42 2.28	2.38 1.77	0.72 1.08	0.24 0.69	0.08
15.00	54.00	R						74.74	30.87	12.61	4.70	2.53	0.76	0.26	0.09
16.00	57.60	v R						7.23 84.46	5.07 34.84	3.53 14.22	2.36 5.30	1.83 2.85	1.12 0.86	0.71	0.46
		v						7.71	5.40	3.76	2.52	1.95	1.19	0.76	0.49
17.00	61.20	R v						94.75 8.19	39.04 5.74	15.91 4.00	5.92 2.67	3.18 2.07	0.96 1.27	0.33 0.81	0.11 0.52
18.00	64.80	R						105.62	43.47	17.70	6.58	3.53	1.06	0.36	0.32
10.00	CO 40	V						8.67	6.08	4.23	2.83	2.19	1.34	0.86	0.55
19.00	68.40	R v						117.06 9.16	48.13 6.42	19.58 4.47	7.27 2.99	3.90 2.32	1.17 1.41	0.40 0.90	0.14 0.58
20.00	72.00	R						129.09	53.03	21.55	7.99	4.29	1.29	0.44	0.15
21.00	75.60	v R						9.64 141.69	6.75 58.15	4.70 23.61	3.14 8.75	2.44 4.69	1.49 1.41	0.95	0.61
		v						10.12	7.09	4.94	3.30	2.56	1.56	1.00	0.64
22.00	79.20	R v							63.51 7.43	25.77 5.17	9.54 3.46	5.11 2.68	1.53 1.64	0.52 1.05	0.18 0.67
23.00	82.80	R							69.09	28.01	10.36	5.55	1.66	0.56	0.19
24.00	86.40	v R							7.77	5.41 30.34	3.62 11.21	2.80 6.00	1.71 1.80	1.09 0.61	0.70
24.00	00.40	N N							8.11	5.64	3.77	2.93	1.60	1.14	0.21
25.00	90.00	R							80.95	32.76	12.10	6.47	1.94	0.65	0.22
26.00	93.60	v R							8.44 87.22	5.88 35.28	3.93 13.02	3.05 6.96	1.86 2.08	1.19 0.70	0.76
		v							8.78	6.11	4.09	3.17	1.93	1.24	0.79

ASSEMBLY GUIDELINES

INITIAL OPERATION

		Dimension	20 mm	25 mm	32 mm	40 mm	50 mm	63 mm	75 mm	90 mm	110 mm	125 mm	160 mm	200 mm	250 mm
		Wall thickness	1.9 mm	2.3 mm	2.9 mm	3.7 mm	4.6 mm	5.8 mm	6.8 mm	8.2 mm	10.0 mm	11.4 mm	14.6 mm	18.2 mm	22.7 mm
l/s	m³/h														
27.00	97.20	R v							93.72 9.12	37.88 6.35	13.97 4.24	7.46 3.29	2.23 2.01	0.75 1.28	0.25 0.82
28.00	100.80	R							100.46	40.57	14.95	7.99	2.38	0.80	0.27
29.00	104.40	v R							9.46 107.42	6.58 43.36	4.40	3.41 8.52	2.08 2.54	1.33 0.86	0.85
		v							9.79	6.82	4.56	3.54	2.16	1.38	0.23
30.00	108.00	R v							114.61 10.13	46.23 7.05	17.01 4.72	9.08 3.66	2.71 2.23	0.91 1.43	0.31 0.91
32.00	115.20	R							10.10	52.25	19.20	10.24	3.05	1.02	0.35
34.00	122.40	v R								7.52 58.62	5.03 21.51	3.90 11.46	2.38 3.41	1.52 1.14	0.97
	122.40	V								7.99	5.34	4.14	2.53	1.62	1.03
36.00	129.60	R v								65.36 8.46	23.96 5.66	12.76 4.39	3.79 2.68	1.27 1.71	0.43
38.00	136.80	R								72.45	26.53	14.12	4.19	1.40	0.47
40.00	144.00	v R								8.93 79.90	5.97 29.22	4.63 15.54	2.83 4.60	1.81 1.54	1.16 0.52
		v								9.40	6.29	4.88	2.98	1.90	1.22
42.00	151.20	R v								87.71 9.87	32.05 6.60	17.03 5.12	5.04 3.13	1.68 2.00	0.57 1.28
44.00	158.40	R								95.87	35.00	18.59	5.49	1.84	0.62
46.00	165.60	v R								10.34	6.92 38.08	5.36 20.21	3.27 5.97	2.09 1.99	1.34 0.67
		v									7.23	5.61	3.42	2.19	1.40
48.00	172.80	R v									41.28 7.55	21.90 5.85	6.46 3.57	2.15 2.28	0.72
50.00	180.00	R									44.61	23.66	6.97	2.32	0.78
52.00	187.20	v R									7.86	6.10 25.48	3.72 7.50	2.38 2.50	1.52 0.84
	107.20	v									8.17	6.34	3.87	2.30	1.58
54.00	194.40	R v									51.65 8.49	27.37 6.58	8.05 4.02	2.68 2.57	0.90 1.64
56.00	201.60	R									55.36	29.32	8.61	2.86	0.96
58.00	208.80	v R									8.80 59.20	6.83 31.34	4.17 9.20	2.66 3.06	1.70 1.02
00.00	200.00	v									9.12	7.07	4.32	2.76	1.76
60.00	216.00	R v									63.16 9.43	33.42 7.31	9.80 4.47	3.25 2.85	1.09 1.82
62.00	223.20	R									67.24	35.57	10.42	3.46	1.16
64.00	230.40	v R									9.75 71.46	7.56 37.78	4.61 11.06	2.95 3.67	1.89 1.23
		v									10.06	7.80	4.76	3.04	1.95
66.00	237.60	R v										40.06 8.05	11.72 4.91	3.88 3.14	1.30 2.01
68.00	244.80	R										42.40	12.40	4.11	1.37
70.00	252.00	v R										8.29 44.81	5.06 13.10	3.23 4.33	2.07 1.45
		V										8.53	5.21	3.33	2.13
75.00	270.00	R v										51.12 9.14	14.91 5.58	4.93 3.57	1.64 2.28
80.00	288.00	R										57.84	16.85	5.56	1.85
85.00	306.00	v R										9.75 64.96	5.95 18.90	3.81 6.23	2.43 2.07
		v										10.36	6.33	4.04	2.59
90.00	324.00	R v											21.06 6.70	6.93 4.28	2.30 2.74
95.00	342.00	R											23.33	7.67	2.55
100.00	360.00	v R											7.07 25.72	4.52 8.45	2.89 2.80
		v											7.44	4.76	3.04
110.00	396.00	R v											30.85 8.19	10.11 5.23	3.35 3.35
120.00	432.00	R											36.42	11.92	3.94
130.00	468.00	v R											8.93 42.45	5.71 13.87	3.65 4.58
		v											9.67	6.18	3.95
140.00	504.00	R v											48.94 10.42	15.96 6.66	5.26 4.26
150.00	540.00	R											55.87	18.20	5.99
160.00	576.00	v R											11.16 63.26	7.14 20.58	4.56 6.76
		v											11.91	7.61	4.87
170.00	612.00	R v											71.10 12.65	23.10 8.09	7.58 5.17

5.2 Simplified procedure

General information

This section describes a simple method suitable to determine the inner pipe diameters for standard installations. The procedure can be applied to all building types, which do not have above-average dimensions. This means that the simplified procedure is suitable for the vast majority of all buildings. The method is applied in the same way for both cold and hot water pipes.

Differentiating calculation procedure

The planner is free to determine the inner pipe diameters through the use of nationally recognised differentiating methods of calculation.

Hot water circulation pipes

Hot water circulation pipes are subject to other hydraulic laws and cannot be measured with this method. Flow velocities in hot water circulation pipes must be determined in accordance with national recommendations or manufacturer guidelines

Load unit

1 load unit (LU) is equal to a tapping point fitting flow rate $\ensuremath{\mathsf{Q}}_{\ensuremath{\mathsf{A}}}$ of 0.1 l/s.

Tapping point fitting flow rates Q_A , minimum draw-off point fitting flow rates Q_{min} and load units for tapping points Table 12

Topping point		Q _{min}	Load unit
Tapping point	l/s	l/s	Loau unit
wash basin, hand basin, bidet, cistern	0.1	0.1	1
household kitchen sink, household washing machine*, dishwasher, utility sink, shower head	0.2	0.15	2
urinal flusher	0.3	0.15	3
bath tub outlet	0.4	0.3	4
garden/garage tap	0.5	0.4	5
commercial kitchen sink DN 20, commercial bath tub outlet	0.8	0.8	8
flusher DN 20	1.5	1.0	15

* for commercial washing machines refer to the manufacturer's recommendations

The values listed above do not correspond to the values provided in product standards. They are merely used for the determination of inner pipe diameters.

Application of the simplified procedure

Starting from the farthest tapping point, the load units for the installation's individual pipe sections must be determined. The load units are then added. The probability of simultaneous use and of peak flow QD has been taken into account in the table of load values. Therefore, the inner pipe diameter can be obtained from the table.

The simplified calculation procedure is based on following flow rates.

Collecting lines, risers, floor level lines	maximum 2.0 m/s
Single supply lines	maximum 4.0 m/s

Note: National regulations may require lower flow rates, in order to prevent pressure surges and noise.


DRINKING WATER HYGIENE

INITIAL OPERATION

Load units LU for the determination of the inner pipe diameters

PP pipe SDR 6													
maximum load value	LU	1	2	3	3	4	6	13	30	70	200	540	970
greatest single value	LU			2			4	5	8				
$d_a \times s$	mm		16 × 2.7	7		20 × 3.4	1	25 × 4.2	32 × 5.4	40 × 6.7	50 × 8.4	63 × 10.5	75 × 12.5
d _i	mm		10.6			13.2		16.6	21.2	26.6	33.2	42	50
maximum pipe length	m	20	12	8	15	9	7						

Example: Determining the inner pipe diameter for standard installations



SYSTEM DESCRIPTION

Table 13

. 61

Implementation

Starting from the farthest tapping point, the load units for the individual pipe sections must be added. Then, the inner pipe diameters are determined.

Definition of tasks in accordance with the installation plan

Calculate the cold water pipe leading from the basement to the tapping points. Calculate the pipeline as required for plastic pipes made of PP.

The following tapping points are installed in every apartment:

- 1 bath tub
- 1 WC with cistern
- 1 wash basin
- 1 household kitchen sink

There are five similar apartments in total.

Solution

The load units are to be determined according to Table 13:

1 bath tub	4 LU
1 WC with cistern	1 LU
1 wash basin	1 LU
1 household kitchen sink	2 LU

Section 1

1 kitchen sink connected	= 2 LU
Table 13 shows 2 LU = pipe 16 mm,	
maximum length 8 m	

Section 2

1 kitchen sink connected	= 2 LU
1 bath connected	= 4 LU
Total	= 6 LU

Table 13 shows 6 LU = pipe 20 mm, maximum length 7 m

Section 3

1 kitchen sink connected	= 2 LU
1 bath connected	= 4 LU
1 wash basin connected	= 1 LU
Total	= 7 LU

Table 13 shows 7 LU = pipe 25 mm

Section 4

1 kitchen sink	= 2 LU
1 bath	= 4 LU
1 wash basin	= 1 LU
1 cistern	= 1 LU
Total for 1 apartment	= 8 LU

Table 13 shows 8 LU = pipe 25 mm

Section 5

2 apartments connected = 16 LU Table 13 shows 16 LU = pipe 32 mm

Section 6

3 apartments connected = 24 LU Table 13 shows 24 LU = pipe 32 mm

Section 7

4 apartments connected = 32 LU Table 13 shows 32 LU = pipe 40 mm

Section 8

5 apartments connected = 40 LU Table 13 shows 40 LU = pipe 40 mm

ASSEMBLY GUIDELINES

6.1 Basic information

6.1.1 Socket welding using a heated tool

Before starting the work, make sure that the welding tools lie flat against the heated rod. Do not use pliers or other unsuitable tools for the assembly, to avoid damage to the coating of the welding tools.

The required welding temperature for processing the POLO-ECOSAN installation system is 250 to 270 °C.

Warning:

- Danger of burns from hot welding equipment
- The first welding should not be carried out until five minutes after the welding temperature has been reached!

POLO-ECOSAN welding equipment and welding tools must be protected against impurities. Burned-on particles can lead to faulty welding connections. Tools may be cleaned with non-fibrous, coarse paper towels. The welding tools must be kept dry at all times.

Damaged and soiled welding tools must be replaced, since only impeccable processing tools can ensure impeccable connections.

Connect the components during the welding process without twisting the parts. Minor corrections can only be made immediately after the parts are connected.

6.1.2 Guidelines

General work protection and accident prevention guidelines are to be observed when using welding equipment.

The Guidelines of the Industrial Trade Associations of the Chemical Industry for Machines for the Processing and Employment of Plastics, Chapter: Welding Machines and Equipment, apply.

For the handling of POLO-ECOSAN welding equipment, machines and tools, the General Guidelines DVS 2208, Section 1 apply. In order to establish a connection between the POLO-ECOSAN pipe and the fitted part, the welding tools used must correspond to the measurements as stipulated by procedure A.

In accordance with DVS Guidelines, control of the necessary application temperature using quick-display surface temperature thermometers is permissible.

6.2 Processing information for welding

Parameters for socket welding with a heated tool

Outer pipe	Insertion depth	Heating) period	Changeover period	Cooling) period
diameter	insertion depth	for SDR 11, SDR 7.4, SDR 6		(maximum period)	fixed	total
mm	mm	at 20°	below +5°	S	S	min
20	14	5	8	4	6	2
25	15	7	11	4	10	2
32	16.5	8	12	6	10	4
40	18	12	18	6	20	4
50	20	18	27	6	20	4
63	24	24	36	8	30	6
75	26	30	45	8	30	6
90	29	40	60	8	40	6
110	32.5	50	75	10	50	8
125	35	60	90	10	60	8

Table 14

Note: heating element temperature 250 to 270 °C

Instructions for socket welding can be found in DVS brochure no. 2207, Section 11, "Socket welding with a heated tool – welding of thermoplastic plastics and pipelines made of polypropylene (PP)". POLO- ECOSAN socket welding is performed according to these guidelines.

In this process, pipes and fittings are welded overlapping. The end of the pipes and fittings are heated using a welding device and are subsequently connected.

SYSTEM DESCRIPTION

TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

SYSTEM REQUIREMENTS

6.2.1 Socket welding with a hand-held welding device, from 20 mm

The following points should be observed:

- The welding device should be equipped with the appropriate welding tools. Welding bushes and core rods have a Teflon coating. In order to avoid damaging the Teflon coating, never use pliers or similar tools for assembly. Please use a suitable hexagon socket wrench.
- 2. Switch on the welding device.
- 3. Using a thermometer or a temperature control pin, check welding temperature before starting to weld.
- 4. The ends of the pipes must be cut straight. Use appropriate pipe scissors or cutters. Pipe, fittings and welding tools must be clean. If necessary, clean them with a lint-free cloth.
- 5. Fitting and pipe must be inserted quickly and axially, without twisting, into the corresponding welding tools. The parts to be welded are then heated without pressure according to the table.
- 6. After the required heating time, fitting and pipe are to be removed quickly from the heating element and connected immediately by pushing together without twisting until insertion depth or markings have been reached. A double roll provides a visual guide to determine the correct welding (see DVS brochure 2207, Section 11). The line markings on the fittings and the pipe ensure the proper alignment of the pipes.
- 7. Pressure due to subsequent installation works must not be exerted upon the welded connection until after the end of the cooling period.
- 8. If necessary, clean the welding tools after each use.







6.2.2 Socket welding with a stationary welding machine, from 40 mm

6.2.2.1 Area of use

We recommend the use of a stationary welding machine for the welding of larger pipe diameters and for the pre-assembly of installation elements. The general guidelines provided by DVS brochure no. 2207, Section 11, "Socket welding with a heated tool. Detailed information on welding times." apply here.

6.2.2.2 Processing steps

- 1. Check the machine: Establish welding insertion depth by setting the dimension; make sure the welding temperature is reached.
- 2. Fix the moulded part with the clamp, taking care not to wind it too tightly, as this can lead to ovality, with a negative impact on the resulting weld. Make sure the moulded part is correctly positioned; use counter-tension to prevent the possibility of slipping.
- 3. Place the pipe loosely into the jaw chuck.
- 4. Adjust the dimension using the rotary button, which sets the precise welding insertion depth.
- 5. Push both tools together until they reach the stop.
- 6. Push the pipe as far as the fitting, then tighten. Make sure that the welding partners are accurately aligned. Open the welding tool.
- 7. Insert the welding device. Using the crank, gradually push the fitting and the pipe into the tool until the stop is reached. Pay attention to the welding time.
- 8. The welding period begins when the pipe and the fitting have been fitted together closely. Allow them to heat up without exerting any further pressure. Once the heating time has elapsed, move the tools apart, remove the welding device, and fit together the fitting and the pipe.
- 9. Observe the required cooling time.









DRINKING WATER HYGIENE

QUALITY MANAGEMENT

INITIAL OPERATION

6.2.3 Welding saddle for 40-250 mm

6.2.3.1 Area of use

- subsequent extension of existing pipe systems
- alternative use instead of tees
- direct branching of a service line to a supply line
- simple assembly of sensor sleeves

6.2.3.2 Processing steps

- 1. Before you start the work, prepare material and tools. Ensure that the welding saddle, the drill and the welding tool have the same diameters.
- 2. Uncover the pipe at the exact location where the welding saddle is supposed to be welded, and mark the welding area. Drain existing pipes and vent the pressure.
- 3. Prepare the welding device and the saddle welding tools for the polyfusion welding and heat to operating temperature (250 to 270 °C).
- 4. Drill through the marked pipe wall with the POLOPLAST Plastic Drill and clear any cuttings from the drill hole.
- 5. The parts and areas to be welded must be clean and dry.
- 6. Push the welding plate into the hole in the wall of the pipe using a suitable and aligned saddle tool, until the tool reaches its stop position. At the same time the weld-in saddle must be pushed in, until the saddle surface reaches the camber of the tool.
- 7. The heating time for the pipe and fittings for the drilled hole dimensions DN 25 and 32 mm is 25 seconds for all dimensions.
- 8. Once the heating time has elapsed, remove the welding device, push the heated weld-in saddle straight into the heated hole as far as it will go without turning it, and hold the pipe in position for at least 20 seconds applying the necessary pressure.
- 9. After a cooling period of at least 10 minutes, the connection can withstand a full load.










6.2.4 Repair plugs

6.2.4.1 Area of use

• the repair of punctured (drilled) pipes

6.2.4.2 Processing steps

- 1. Drain pipes.
- 2. Uncover damaged pipe.
- 3. Drill damaged area of pipe out to a diameter of 8 mm at a right angle to the pipe.
- 4. Heat up drill hole and repair plug with POLO-ECOSAN hole welding tool for 15 seconds.
- 5. Insert repair plug immediately.
- 6. Cut off protruding end of repair plug.
- The repaired area of pipe has reached full strength after approx.
 5 minutes.



DRINKING WATER HYGIENE

6.2.5 Use of electric welding sockets

6.2.5.1 Area of use

- welding in constrained positions and in areas with restricted space
- repair welding
- alternative processing option for large pipe dimensions

6.2.5.2 Preparation

1. General information and controls

Cleanliness – besides the correct operation – is the most important requirement for achieving good welding results! For the sockets to stay thoroughly clean, they need to be left in the original packaging until they are used. Furthermore, the surface of the pipe must be clean and undamaged. Incorrectly collapsed pipe ends must be cut off. We recommend PP-cleaner or cloths with ethyl alcohol for cleaning.

The pipe elements to be welded as well as the electric socket and the welding equipment must show precisely the same temperature level within the permitted temperature range (i.e. + 5 °C to 40 °C according to DVS 2207). (UV radiation or improper storage, to name two examples, can cause significant differences in temperature, which will result in faulty welding.)

2. Preparatory work

- It is absolutely mandatory to maintain the order of the working steps!
- 1. Cut pipe ends at a right angle and burr them (control carved ends).
- 2. Remove any dirt from the pipe ends at the required length and dry them.
- 3. Mark the insertion depth of the electro-welded sockets at the pipe end.
- 4. Use a pipe scraper to remove the oxide film from the entire exposed pipe surface down to the marked insertion depth.
- 5. Clean thoroughly using ethyl alcohol. A homogeneous and impermeable welded connection can only be established, if the surface in the welding range is peeled and cleaned comprehensively.

Do not touch peeled pipe ends again and protect them from new contamination – e.g. put a clean plastic bag over them. Weld within 30 minutes after the peeling process.

3. Assembly of the electric welding socket

- 1. Carefully clean the inner surface of the socket using lint-free cloth. Mount the socket within 30 minutes after opening the packaging.
- 2. Slide the electric welding socket onto the clean and dry pipe end until you reach the marked insertion depth.
- 3. Completely remove the protective foil and slide the peeled and clean second pipe end into the electric welding socket.

Contaminations are to be avoided diligently and all parts must be securely fastened. Pipes must be free of flexural strain or self-weight when they are inserted into the electric welding socket. The socket should still be able to move the pipe ends after the mounting process. The air gap must be evenly distributed around the circumference. A joint that is not free of tension or that has shifted can result in undesired molten mass or in an inadequate connection. The pipe ends and welded sockets must be dry when mounted.





DRINKING WATER HYGIENE

PLANNING AND DESIGN

. 69

4. Welding process

- 1. Position the socket so that the air gap is evenly distributed around the circumference.
- 2. Set the welding equipment to the diameter of the welding socket.
- 3. Compare the data on the welding equipment's display screen with the details on the label; enter the required code manually or by scanning it (see barcode label on the electric welding socket).
- 4. Start the welding process and monitor it closely.

The joint must not be moved or put under external pressure during the entire welding process, until it has completely cooled off! Once the welded connection has been successfully established, two pins remain visible as an outward sign.

5. Cooling-off time and pressure test

The welded pipe joint may only be put under pressure or moved, and the fastening may only be loosened once the cooling-off period has elapsed!



The minimum required cooling-off time is marked on the electric welding sockets. In case of ambient temperatures above 25 °C or when there is strong solar radiation, the cooling-off time must be extended accordingly!

In order to achieve an ideal and stable welding result, both pipe ends must be plane-parallel within the electric welding socket! It is imperative to mark the socket insertion depth on the pipe, and to adhere to it!

Type of strain	Compression strain	Minimum waiting period
Tension, bending, torsion of unpressurised pipelines		20 minutes
Testing or working pressure of pressurised pipelines	up to 0.1 bar	20 minutes
	0.1 bar to 1 bar	60 minutes
	over 1 bar	120 minutes
Repetition of welding process		60 minutes

6.2.6 Butt welding machine for 160 mm and above

Please also refer to the operating instructions for your welding equipment, which will provide the precise welding parameters.

Processing steps

- 1. Protect the workplace against the effects of weather and against contamination by dirt.
- 2. Heat up the welding machine and check for proper function.
- 3. Cut the pipes at a right angle to the required length.
- 4. Align the pipes and tighten the clamping elements.
- 5. Using a milling machine, plane the front of the pipes at a uniform level and evenly.
- 6. Remove shavings and clean the front side with ethyl alcohol.
- 7. Maintain pipe offset (at most 0.1 × wall thickness).
- 8. Combine the pipes and check for a seamless connection (maximum tolerance 0.5 mm).
- 9. Set the joining pressure (refer to relevant table in the operating instructions of the welding machine).
- 10. Check welding temperature (210 °C).
- 11. Examine cleanliness of heated element before every operation.
- 12. Initiate welding process by swivelling the heated element and press the pipes onto the heating element using joining pressure.
- 13. After reaching the bead height, the pressure is reduced. This is the start of the warm-up time, which brings the pipe ends to the required welding temperature.
- 14. Once the warm-up time has elapsed, remove the heated element swiftly, and combine the pipes using the necessary pressure.
- 15. The pipes are now welded and will cool down under pressure.
- 16. Do not release or remove the welded joint from the clamps until the stipulated cooling-off period has elapsed.









ASSEMBLY GUIDELINES

7.1 Fastening techniques

A pipe fastening system that complies with regulations is subject to the following requirements:

- The fastening system must absorb any forces that may occur.
- The external impact upon pipes and fittings, caused e.g. by sagging, changes in length,
- mechanical load, must be prevented by applying appropriate fastening techniques.
- The pipework must be held firmly in the intended position.

The fastening mechanism must be selected in accordance with the outside diameter of the pipe due to be fixed into position. Take appropriate measures to ensure that the pipe surface cannot be damaged by any of the pipe fastening elements.

Experience has shown that pipe clamps with rubber inserts represent the ideal fastening mechanism for POLOPLAST installation systems. In the selection of suitable fastening materials, we generally differentiate between fixed bearings and slide or guide bearings.

7.1.1 Fixed points

- Fixed points are determined to divide the pipe line into individual sections, which helps to avoid uncontrolled pipe movement.
- These fixed points need to be designed so as to compensate for the expansion forces arising from the pipe and possibly existing additional loads.
- Short distances in the ceiling should be chosen as the clamp and the fastening element need to be fastened tightly because of the forces that arise here.

7.1.2 Sliding points

- They have to compensate for the axial pipe movement without causing any damage.
- When positioning the sliding points, care must be taken that no fittings or fixtures obstruct the pipeline movement.

WELDING TECHNOLOGY

INITIAL OPERATION

7.2 Mounting distances

Tables for the determination of the distance between clamps, depending on temperature and outside diameter. The values specified are POLOPLAST recommendations, and are valid for horizontal and vertical installations.

	Media temperature [°C]						
Dimension in mm	10	20	30	40	50	60	70
			Mour	nting distances	; [cm]		
20	80	70	65	65	65	60	60
25	90	80	75	75	75	70	70
32	100	90	85	85	85	80	80
40	110	100	95	95	95	90	90
50	140	120	115	110	105	100	100
63	160	140	130	125	120	110	110
75	180	150	140	135	130	120	120
90	210	160	150	150	140	130	130
110	240	180	170	160	150	140	140
125	260	200	185	170	160	150	150

POLO-ECOSAN pipes SDR 6, SDR 7.4, SDR 11

POLO-ECOSAN pipes with pipe supports SDR 6, SDR 7.4, SDR 11

	Media temperature [°C]			
Dimension in mm	10	70		
	Mounting dis	stances [cm]		
20	170	150		
25	200	180		
32	220	200		
40	230	210		
50	230	230		
63	230	230		
75	230	230		
90	230	230		
110	230	230		

. 73

	Media temperature [°C]						
Dimension in mm	10	20	30	40	50	60	70
			Mour	nting distances	[cm]		
20	110	95	90	85	85	80	70
25	120	105	105	95	95	90	80
32	140	120	120	110	110	105	95
40	160	140	135	125	125	120	110
50	185	155	155	145	145	135	130
63	200	175	175	165	165	155	145
75	215	190	190	175	175	165	155
90	230	210	210	195	195	180	180
110	250	220	220	210	200	200	190
125	250	240	225	215	195	185	170
160	280	270	245	235	205	195	180
200	285	275	250	240	210	205	185
250	290	280	255	245	215	200	190

POLO-ECOSAN ML5 and POLO-ECOSAN ML3 pipes, SDR 7.4, SDR 11

7.3 Laying the pipes

In the case of pipes laid in walls and ceilings, the friction forces that occur prevent the expansion of the pipes, and therefore no compensation is necessary. The resulting tension is absorbed by the pipe materials.

Due to the low expansion forces, the masonry or the plaster are not damaged.

Installing pipes in a shaft

- Changes in length can be disregarded if pipes are laid in a vertical shaft.
- It will be sufficient to mount a fixed-point clamp ahead of every branching; in a rising pipe, all clamps are fixed points.
- Rising pipes can be laid without expansion elbows.
- The distance between two fixed points must not be greater than 3 m.


Open laying of pipes

- Such pipes need to be laid using fixed and slide points. This will ensure sufficient space for the pipe to expand.
- If the line length equals or exceeds 40 m, expansion must be compensated for using bending legs and angles.

Concealed laying

• No precautions required.







WELDING TECHNOLOGY

QUALITY INITIAL MANAGEMENT OPERATION

Length variation 7.4

Changes in the length of pipes are dependent on the increasing temperature of the pipe material. This temperature change can be caused by different installation and operating temperatures, as well as varying media temperatures. The potential variation in length must be taken into account at the time of installation.

If the operating temperature is higher than the installation temperature, the pipe will elongate. If the media temperature (e.g. cold water) is lower than the installation temperature, the calculation will result in a reduction in length.

The following factors must be considered in the calculation of the variation in length:

- installation temperature
- operating temperatures (media temperatures)
- temperature difference between installation and operating temperatures
- coefficient of linear expansion
- pipe length

The coefficient of linear expansion α for POLO-ECOSAN pipes are:

- POLO-ECOSAN pipe
- $\alpha = 0.15 \text{ mm/mK}$ • POLO-ECOSAN pipe with pipe support $\alpha = 0.05 \text{ mm/mK}$

 $\alpha = 0.05 \text{ mm/mK}$

 $\alpha = 0.038 \text{ mm/mK}$

- POLO-ECOSAN ML3 pipe
- POLO-ECOSAN ML5 pipe

The formula for the calculation of the variation in length is:

	$\Delta L = \alpha \times I_0 \times \Delta T$					
ΔL	variation in length	mm				
I ₀	pipe length prior to temperature change	m				
α	length variation coefficient	$\frac{mm}{m \times K}$				
ΔT	maximum occurring temperature difference between installation and operating temperature	К				

Example: POLO-ECOSAN SDR 6 Length: 14 m Installation temperature: 20 °C Operating temperature: 60 °C

I = 0.15 mm × 14 m × (60 - 20) K $\overline{m \times K}$ I = 84 mm

Calculation with ML5 Pipe: l = 21.28 mm

Linear expansion tables

POLO-ECOSAN pipe								
pipe length	difference in temperature ∆T (K)							
in meters (m)	10	20	30	40	50	60	70	80
1.0	1.5	3.0	4.5	6.0	7.5	9.0	10.5	12.0
2.0	3.0	6.0	9.0	12.0	15.0	18.0	21.0	24.0
3.0	4.5	9.0	13.5	18.0	22.5	27.0	31.5	36.0
4.0	6.0	12.0	18.0	24.0	30.0	36.0	42.0	48.0
5.0	7.5	15.0	22.5	30.0	37.5	45.0	52.5	60.0
6.0	9.0	18.0	27.0	36.0	45.0	54.0	63.0	72.0
7.0	10.5	21.0	31.5	42.0	52.5	63.0	73.5	84.0
8.0	12.0	24.0	36.0	48.0	60.0	72.0	84.0	96.0
9.0	13.5	27.0	40.5	54.0	67.5	81.0	94.5	108.0
10.0	15.0	30.0	45.0	60.0	75.0	90.0	105.0	120.0
15.0	22.5	45.0	67.5	90.0	112.5	135.0	157.5	180.0
20.0	30.0	60.0	90.0	120.0	150.0	180.0	210.0	240.0
25.0	37.5	75.0	112.5	150.0	187.5	225.0	262.5	300.0
30.0	45.0	90.0	135.0	180.0	225.0	270.0	315.0	360.0
35.0	52.5	105.0	157.5	210.0	262.5	315.0	367.5	420.0
40.0	60.0	120.0	180.0	240.0	300.0	360.0	420.0	480.0
45.0	67.5	135.0	202.5	270.0	337.5	405.0	472.5	540.0
50.0	75.0	150.0	225.0	300.0	375.0	450.0	525.0	600.0
	linear expansion ΔL in mm							

		POLO-E	ECOSAN pipe w	ith pipe suppor	t, POLO-ECOSA	N ML3		
pipe length	difference in temperature ∆T (K)							
in meters (m)	10	20	30	40	50	60	70	80
1.0	0.5	1.0	1.5	2.0	2.5	3.0	3.5	4.0
2.0	1.0	2.0	3.0	4.0	5.0	6.0	7.0	8.0
3.0	1.5	3.0	4.5	6.0	7.5	9.0	10.5	12.0
4.0	2.0	4.0	6.0	8.0	10.0	12.0	14.0	16.0
5.0	2.5	5.0	7.5	10.0	12.5	15.0	17.5	20.0
6.0	3.0	6.0	9.0	12.0	15.0	18.0	21.0	24.0
7.0	3.5	7.0	10.5	14.0	17.5	21.0	24.5	28.0
8.0	4.0	8.0	12.0	16.0	20.0	24.0	28.0	32.0
9.0	4.5	9.0	13.5	18.0	22.5	27.0	31.5	36.0
10.0	5.0	10.0	15.0	20.0	25.0	30.0	35.0	40.0
15.0	7.5	15.0	22.5	30.0	37.5	45.0	52.5	60.0
20.0	10.0	20.0	30.0	40.0	50.0	60.0	70.0	80.0
25.0	12.5	25.0	37.5	50.0	62.5	75.0	87.5	100.0
30.0	15.0	30.0	45.0	60.0	75.0	90.0	105.0	120.0
35.0	17.5	35.0	52.5	70.0	87.5	105.0	122.5	140.0
40.0	20.0	40.0	60.0	80.0	100.0	120.0	140.0	160.0
45.0	22.5	45.0	67.5	90.0	112.5	135.0	157.5	180.0
50.0	25.0	50.0	75.0	100.0	125.0	150.0	175.0	200.0
				linear expans	ion ΔL in mm	·		

76 .

POLO-ECOSAN ML5. POLO-UV ML5								
pipe length	difference in temperature ∆T (K)							
in meters (m)	10	20	30	40	50	60	70	80
1.0	0.4	0.8	1.1	1.5	1.9	2.3	2.7	3.0
2.0	0.8	1.5	2.3	3.0	3.8	4.6	5.3	6.1
3.0	1.1	2.3	3.4	4.6	5.7	6.8	8.0	9.1
4.0	1.5	3.0	4.6	6.1	7.6	9.1	10.6	12.2
5.0	1.9	3.8	5.7	7.6	9.5	11.4	13.3	15.2
6.0	2.3	4.6	6.8	9.1	11.4	13.7	16.0	18.2
7.0	2.7	5.3	8.0	10.6	13.3	16.0	18.6	21.3
8.0	3.0	6.1	9.1	12.2	15.2	18.2	21.3	24.3
9.0	3.4	6.8	10.3	13.7	17.1	20.5	23.9	27.4
10.0	3.8	7.6	11.4	15.2	19.0	22.8	26.6	30.4
15.0	5.7	11.4	17.1	22.8	28.5	34.2	39.9	45.6
20.0	7.6	15.2	22.8	30.4	38.0	45.6	53.2	60.8
25.0	9.5	19.0	28.5	38.0	47.5	57.0	66.5	76.0
30.0	11.4	22.8	34.2	45.6	57.0	68.4	79.8	91.2
35.0	13.3	26.6	39.9	53.2	66.5	79.8	93.1	106.4
40.0	15.2	30.4	45.6	60.8	76.0	91.2	106.4	121.6
45.0	17.1	34.2	51.3	68.4	85.5	102.6	119.7	136.8
50.0	19.0	38.0	57.0	76.0	95.0	114.0	133.0	152.0
				linear expans	ion ΔL in mm			

7.5 Thermal expansion force

The following formula can be used to calculate the thermal expansion force:

 $F_t = \frac{E \times A \times \alpha \times \Delta T}{1000}$

 F_t = thermal expansion force [N]

E = modulus of elasticity (modulus of rigidity) [MPa = N/mm²]

A = cross-sectional area of the pipe in [mm²]

 α = specific thermal expansion coefficient [mm/(mK)]

 ΔT = temperature difference resulting from media temperature minus laying temperature [K]

Material	Pipe dimension	Modulus of elasticity	Coefficient of linear expansion	Thermal Expansion Force
Steel	26.9×2.65	220,000	0.012	533
High-grade steel	22.0 × 1.2	200,000	0.015	235
Copper	22.0 × 1.0	130,000	0.016	137
Prostab	25.0 × 3.5	3,500	0.035	29
PVC	25.0 × 3.2	1,100	0.08	19
PP-R / PP RCT	25.0 × 4.2	900	0.150	12
PE-X	25.0 × 3.5	540	0.175	22
PE-RT	25.0 × 3.5	250	0.180	10
PE-X / Alu	26.0 × 3.0	3,500	0.030	22

SYSTEM DESCRIPTION

This comparison shows that the thermal expansion forces occurring in plastic pipes are extremely low, compared to pipes made of metallic materials

If the thermal expansion force is countered by a corresponding retention force, the expansion can be neutralised effectively.



7.6 Expansion compensation

Variations in length caused by temperature differences must be taken into account during the planning stage to prevent subsequent damage to pipelines, fastening elements and the building structure. In order to keep the occurring stress impacts within acceptable ranges, the variation in length must be compensated appropriately. There are two options available to achieve this compensation:

- Expansion compensation using bending legs and a U-pipe bends ("natural" expansion compensation)
- Expansion compensation using compensators ("artificial" expansion compensation)

In most cases, directional changes in the pipe routeing can be utilised to absorb the variation in length. Should the directional changes not be sufficient, a U-pipe bend must be used.

It is important to bear in mind that the outlets distributed throughout the line system can also influence the variation in length, or may be negatively affected themselves by the variation in length.

Please refer to the manufacturers of the compensators for more information on the expansion compensation provided by compensators.


7.6.1 Bending legs

In order to determine the specific direction in which the expansion compensation is steered, the directional change is installed between two fixed points. Generally, the pipes are arranged in right angles at the points where the direction changes. A variation in the length of one leg produces bending in the other leg. Provided that all legs are of a sufficient length to prevent the resulting flexural strain from becoming too great, the system can flexibly absorb the variation in length.

	$I_{\rm B} = K \times \sqrt{d \times \Delta L}$	
I _B	length of the bending leg	mm
K	material-dependent constant (15.0 for PP)	
d	outside pipe diameter	mm
ΔL	variation in length	mm

Sample calculation: Pipe outside diameter 75 mm Variation in length 84 mm

 $I_B = 15 \times \sqrt{75} \text{ mm } 84 \text{ mm}$ $I_B = 1191 \text{ mm}$



78.

WELDING TECHNOLOGY


INITIAL OPERATION

MANAGEMENT

7.6.2 Expansion loop

If it is not possible to compensate for the variation in length by introducing directional changes into the pipe routeing, an expansion loop must be used instead.


For the implementation of the expansion loop, the length I_B of the bending leg and the width b_{min} of the expansion loop must be considered. It is advisable to position the expansion loop in such a way that the lengths I_1 and I_2 are equal.



7.6.3 Pre-tensioning

If, during installation, an expansion loop is already pre-stretched by the length ΔL_v against the subsequent length variation and is thus "pre-tensioned", the length of the bending leg I_{BV} can be reduced.

	$I_{BV} = I_{B} \times \sqrt{1 - \frac{\Delta L_{V}}{\Delta L}}$	
ΔL_v	variation in length with pre-tensioning	mm
ΔL	variation in length	mm
I _{BV}	length of bending leg with pre-tensioning	mm
I _B	length of bending leg	mm



Sample calculation: Variation in length $\Delta L = 84$ mm Pre-tensioning $\Delta L_V = 42$ mm

$I_{BV}=1191~mm \int$	$\times 1 \frac{42}{84}$ mm
$I_{BV} = 842 \text{ mm}$	

7.7 Insulation

The EnEV (German Energy Saving Regulation) standard regulates the thermal insulation of pipelines and fittings within the Federal Republic of Germany. The purpose of the pie insulation is to:

- Protect the pipes against condensation
- · Protect the cold water pipes against exposure to heat
- Minimize heat losses
- Reduce the transfer of heat to structural components
- Reduce sound transmission
- Protect against UV radiation
- Absorb variations in length caused by temperature
- Protect against mechanical stresses
- Protect against corrosion

7.7.1 Hot water insulation

Requirements according to EnEV

Table 15: Thermal insulation of heat distribution and hot water pipelines as well as fittings.

Table 15

Line	Type of pipeline / valves and fittings	Minimum thickness of the insulation layer, based on a thermal conductivity of 0.035 W/(m k)
1	Inner diameter up to 22 mm	20 mm
2	Inner diameter above 22 mm up to 35 mm	30 mm
3	Inner diameter above 35 mm up to 100 mm	equal to inner diameter
4	Inner diameter above 100 mm	100 mm
5	Pipes, valves and fittings acc. to lines 1 to 4 in wall and ceiling breaks, at the intersection of lines, at line connection points, at central mains system switches	$\frac{1}{2}$ of the requirements listed in lines 1 to 4
6	Central heating pipes acc. to lines 1 to 4, that have been installed in buildings between heated rooms of various users since January 31, 2002	$\frac{1}{2}$ of the requirements listed in lines 1 to 4
7	Pipes acc. to line 6 installed in floor constructions	6 mm
8	Cold distribution and cold water pipes as well as fittings for ventilation and cooling systems	6 mm

When using materials with thermal conductivity values other than 0.035 W/(m K), the minimum thickness values of the insulation layers must be converted accordingly. The calculation methods and values contained within accepted engineering standards must be employed for the conversion and the thermal conductivity of the insulation material.

In the case of heat distribution and hot water pipes, as well as cold distribution and cold water pipes, the minimum thickness values of the insulation layers listed in Table 5 may be reduced to the extent of the equivalent limitation of heat absorption or loss, and the insulating effect of the pipe walls must be taken into account.

7.7.2 Cold water insulation

Guide values for the minimum thickness of insulating layers used to insulate cold drinking water systems against heat and condensation.

Insulation layer thickness acc. to DIN 1988-200, Table 16

Installation situation Insulation layer thickness at $\lambda = 0.040$ W/mK* Exposed pipes in unheated rooms (e.g. basement) 9 mm Exposed pipes in heated rooms 13 mm Pipes installed in a duct, without pipes carrying high-temperature media 13 mm Pipes installed in a duct, alongside pipes carrying high-temperature media 13 mm Pipes installed in wall slots, rising pipes 4 mm Pipes installed in wall recesses, alongside pipes carrying high-temperature media 13 mm Pipes installed on concrete floor (also alongside non-circulating hot water lines) 4 mm

*) If materials with different thermal conductivity coefficients are used, the insulation layer thickness must be converted accordingly in relation to a pipe diameter of d = 20 mm.

The temperature increase of drinking water is primarily influenced by the duration of stagnation, the position and arrangement of the pipes, and by the insulation used. Care must be taken during installation of pipelines to maintain a sufficient distance to all heat sources such as warm pipes, flues, and heating pipes.

In the case of standing water, even insulation measures cannot provide long-term protection against warming.

7.7.3 Dew point

Condensation occurs when the temperature of a surface falls below the saturation temperature of the surrounding air.

The saturation temperature of the air is determined from the current temperature and the relative humidity. The temperature of the surface is determined by the heat transfer from the material to the pipe surface, from the air to the pipe surface, and the heat transfer through the pipe wall.

Data required in order to determine the dew point:

- Relative air humidity
- Ambient temperature
- Water temperature
- Temperature difference $\Delta \vartheta$ in K (room temperature water temperature)

Sample calculation:

At an ambient temperature of 27 °C, 60 % relative humidity and 12 °C water temperature the pipe begins to sweat.

- For SDR 6 pipes the maximum temperature difference is 15 K.
- For SDR 11 pipes the maximum temperature difference is 11 K.

Table 16





Diagram for the determination of the dew point for POLO-ECOSAN SDR 6

Diagram for the determination of the dew point for POLO-ECOSAN SDR 11



SYSTEM DESCRIPTION

WELDING TECHNOLOGY

INITIAL OPERATION

7.8 Noise protection

In order to prevent the transmission of structure-borne noise from the pipe system to the building, sound insulation preventing structure-borne sound must be applied to the pipes. This can be achieved through tape bindings, insulating hoses or through sheathed half-shells. This type of insulation dampens the transmission of flow noise as well as noises from machine parts (pumps) to the structural components surrounding the pipes. Standard DIN 4109 with Supplementary Table A1 regulates the minimum requirements of sound insulation in buildings, given varying requirements and taking into account the source of noise. The following sound pressure levels in dB(A) are admissible.

Admissible sound pressure levels in rooms requiring sound protection against noise from building services and commercial enterprises

	Characteristic sound pressure level dB(A) in		
Source of noise	Living rooms and bedrooms	Teaching and working spaces	
Plumbing applications (both water supply- and wastewater systems)	$\leq 30^{(1)} 2^{(1)}$	≤ 35 ^{1) 2)}	
Other building services systems	≤ 30 ³⁾	≤ 35 ³⁾	
Businesses during the day 6 a.m. to 10 p.m.	≤ 35	≤ 35 ³⁾	
Businesses during the night 10 p.m. to 6 a.m.	≤ 25	≤ 35 ³⁾	

¹⁾ Single, short-term spikes that occur when operating valves and devices in accordance with Table 6 DIN 4109 (opening, closing, adapting, interrupting, etc.) can be disregarded at this time.

Conditions stipulated in the contract for work to meet the admissible installation sound pressure level:

 The construction documents must take into account the requirements of noise protection, which means that – amongst other requirements to be observed – the necessary sound insulation certificates must be provided for the components used.

• Furthermore, construction management must be named and involved before an installation is closed in or covered. Further details are regulated by the ZVSHK Bulletin (Central Association for Plumbing, Heating, Air Conditioning).

³ In the case of ventilation systems the values are permitted to be 5 dB(A) higher, provided that the noise is constant noise, without distinct audible sounds.

7.9 Fire protection

The POLO-ECOSAN installation system is classified as follows:

Standard	Classification
EN 13501	E
DIN 4102	B2

EN 13501 and DIN 4102

These standards define the classification of those materials, which are used as products or as product components in building construction. The fire behaviour of the products used is tested and classified by testing the behaviour in the case of fire, e.g. the development and spread of fire and smoke.

The behaviour of PP-R in the case of fire

Pipes and fittings made of PP-R, PP-RCT and with fibres, do not exhibit an increased conflagration gas toxicity. In construction objects with a greater need for fire protection measures, pipe ducts through walls and ceilings must be protected against fire in such a way that, as a general principle, all pipe ducts have the same classification as the structural components through which the ducts lead.

For example: In the case of a wall, which features a fire resistance period of 90 minutes (F90), the pipe ducting must also have a fire resistance period of 90 minutes (R 90).

All fire protection systems that have been issued with a corresponding accreditation can be used with POLO-ECOSAN pipes.

One possible solution is the fire protection measure using fire protection collars or special mineral insulation with a melting temperature of > 1,000 $^{\circ}$ C.



Table 17

Fire load

The resulting combustion heat V(kWh/m) of POLO-ECOSAN pipes is dependent on the pipe dimension. The basis for the calculation of the combustion heat V for POLO-ECOSAN pipes made of PP-R is given by the lower calorific value Hu = 12.2 kWh/kg (acc. to DIN 18230 Section 1), as well as the material mass m (kg/m).

Combustion values V (kWh/m) of POLO-ECOSAN pipes, Table 17

Outer	PP R			
diameter	SDR 11	SDR 6	SDR 7.4	
20	1.31	2.1	1.80	
25	2	3.25	2.79	
32	3.25	5.3	4.44	
40	5.03	8.19	6.95	
50	7.78	12.81	10.84	
63	12.32	20.13	17.05	
75	17.32	28.55	24.25	
90	24.77	41	34.76	
110	36.72	61.49	51.88	
125	47.54	77.84		

SYSTEM DESCRIPTION

8.1 Pressure-tests

Upon completion of the installation work, drinking water installations inside buildings must be subjected to hydraulic pressure testing. This must be carried out while the pipe system is fully accessible. In accordance with DIN EN 806, the test can be carried out using water or, if national regulations permit, with oil-free clean air at low pressure or inert gases.

The choice of method to be applied must take into account the factors relating to hygiene and corrosion, and must be determined in relation to the design of the system and the time schedule of the construction project.

In order to pressure-test using water, the completed pipelines must be gradually filled with drinking water that does not contain particles \geq 150 µm, and must then be vented. The drinking water system must be put into operation immediately after the pressure test with water and the subsequent flushing of the system. If this is not possible, the flushing process must be repeated regularly, with no more than 7 days between repetitions. If the system is due to be put into operation at a later stage, in the interest of hygiene, the pressure test should be conducted with air or inert gas as a testing medium.

Due to the characteristic properties of the materials used, plastic pipes expand for a limited period of time when they are subjected to pressure. This has an impact on the test result. A change in the temperature in a pipe system can lead to a change in pressure in the case of pipes made of plastic. Consequently, pressure testing should follow the protocols provided below (page 86 and following).

Once the pressure tests have been completed, the responsible technician must produce a formal record, which includes an assessment of the test. The impermeability of the system must be evident, and must be confirmed in writing.

Pressure testing with water

DIN EN 806-4 stipulates that there are three possible pressure tests, depending on the different material properties. Due to issues concerning the practical feasibility on site, and following practical experiments, a modified method was selected, which is suitable for all materials and all material combinations. The duration of the test was extended beyond the period stipulated in the standard, to ensure that even the smallest possible leaks can be detected during the leak test.

Pressure testing with air

As gases are compressible, when carrying out pressure testing using air, the accident prevention regulations "Working on Gas Installations" and the guidelines "Technical Rules for Gas Installations DVGW-TRGI" must be observed for physical and safety reasons. Therefore, acting in agreement with the responsible professional association and in observance of this body of rules, the testing pressures were fixed at a maximum of 0.3 MPa (3bar), corresponding to the stress and leak tests for gas lines. This fully complies with the national regulations.

The volume in the pipe system has a significant impact on the pressure results shown. Changes in temperature can also influence the test results. A high pipe system volume can have a negative impact on the determination of minor leaks using drops in pressure. Consequently, it can be helpful to divide the test into small sections, in order to achieve the best possible testing safety and accuracy.

Pressure testing protocol, testing media: water

Construction project:
Construction stage:
Client represented by:
Contractor represented by:
Admissible operating pressure = 10 bar bar (if higher)
Water temperature °C Ambient temperature °C
System inspection as Complete system I in sections

Preliminary arrangements:

- □ The pipe system is made of PP, and, if applicable, with combined installations made of metal and multi-layer composite pipelines.
- \Box All pipes have been sealed by metal plugs, caps, blanking plates or blank flanges.
- Equipment and valves that do not meet the required test pressure, have been separated from the lines.
- □ Expert laying of the piping.
- $\Box\,$ Filling water has been filtered. Filter mesh < 150 μm
- $\hfill \Box$ The system has been filled, flushed and de-aerated.

Leak test

	Testing method	Results	Note	
	Preliminary test Test pressure 15 bar Test duration 30 min	A maximum pressure drop of 0.5 bar Test pressure after 30 min bar		
	Main test Test pressure 10 bar Test duration 30 min	A maximum pressure drop of 0.2 bar Test pressure after 30 min bar		
	Final test Test pressure 10 bar Test duration 60 min	No pressure drop Test pressure after 60 min bar		
 Visual inspection of pipe system has been carried out No leaks were determined during the testing period The pipe system is leak-proof 				
Dlago		Data		

Place	Date
Client	Contractor
1) The pressure gauges used must allow a precise reading of	of a 0.1 bar change in pressure.

WELDING TECHNOLOGY

Pressure testing protocol testing media compressed air or inert gas
Construction project:
Construction stage:
Client represented by:
Contractor represented by:
Pipe system materials:
System operating pressure bar ambient air temperature °C
Temperature of testing medium °C
Testing medium \Box oil-free compressed air \Box nitrogen \Box carbon dioxide
System inspection as Complete system C in sections
 Preliminary arrangements: All pipes have been sealed with metal plugs, caps, blanking plates or blank flanges. Equipment, pressure tanks or drinking water heaters have been disconnected from the system. A visual inspection ensuring the professional execution of all pipe connections has been carried out.
 1. Leak test ¹) Testing pressure 150 mbar Up to 100 litres pipe system capacity require a testing period of at least 120 minutes. For every further 100 litres, the testing period must be extended by 20 minutes.
 Pipe system capacity: litres Testing period: minutes The testing period starts, once the testing pressure has been reached, taking into account a waiting period for the equalization of the media temperature and the ambient temperature. Visual inspection of pipe system has been carried out Inspection by pressure gauge, U-pipe or respectively standpipe water column has been carried out ¹⁾ No drop in pressure was determined during the testing period No leaks were determined during the testing period
 2. Strength test with elevated pressure ²) Wait for temperature equalization and steady state in the case of plastic pipes; the testing period starts once these have been reached. Testing pressure ≤ 63 mm maximum 3 bar Testing period: 10 minutes
 No drop in pressure was determined during the testing period No leaks were determined during the testing period The pipe system is leak-proof
Place Date
Client

8.2 Flushing the system

On principle, drinking water installations must be thoroughly flushed immediately upon completion, irrespective of the materials used. Flushing the system ensures that the following requirements are observed:

- Protection of drinking water quality
- Prevention of corrosion damage
- Prevention of functional damage to valves, fittings and equipment
- Cleaning of the inner surface of the pipes

According to EN 806-4 "Specifications for installations inside buildings conveying water for human consumption", it is necessary to flush the system for drinking water installations as soon as possible upon completion and immediately before putting them into operation. The following regulations must be observed.

- Perform the flushing on warm and cold water systems separately.
- The water must be filtered. The water must not contain any particles > 150 µm, as these can cause damage to the system.
- If the system is not put into operation immediately after the system is flushed, the flushing process must be repeated regularly, with no more than 7 days between repetitions.

Two flushing methods have proven successful in practice:

- 1. Flushing with water
- 2. Flushing with a water/air mixture

The following factors must be considered when applying method "1. Flushing with water":

- Jet regulators, sieves, flow regulators, shower heads or hand-held showers must be dismantled in order to protect them from damage and soiling, and to ensure the maximum possible flow through the pipes.
- All valves and shut-off devices must be fully opened.
- If the system rinse is carried out in sections, it must be started on the lowest floor and continued upwards, moving from floor to floor.
- During the rinsing process the minimum flow rate must be 2 m/s.
- The water content of the system must be completely exchanged at least 20 times.
- When opening the draw-off points, the first draw-off point to be opened must be the one furthest away from the rising pipe.
- Draw-off points are closed in the reverse order: moving from the rising pipe to the end.
- Each draw-off point must be fully opened.

8.3 Initial operation

- Do not fill the system with water until standard operation is imminent.
- Delays cause a hygienic risk. Flushing schedules or forced flushing should be carried out to ensure that the water is exchanged regularly.
- The operator should receive the basic planning documents, the records of leak and stress tests, as well as all flushing and training documents at the same time as the operating instructions.
- The operator must be informed that the regular exchange of the water must be ensured.
- The operator must be advised of the dangers presented by a microbiological contamination of then system caused by hot water temperatures that are too low, and cold water temperatures that are too high.
- The operator should be offered a maintenance contract.

PLANNING AND DESIGN

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

GEMENT

Initial operation protocol: flushing with wa	ter						
Construction project:							
Construction stage:							
Client represented by:							
Contractor represented by:							
Pipe system materials:							
Guide values for the minimum number of draw-off point largest nominal width of the distribution pipe	ts to be	e opene	ed, with	n refere	nce to	the	
Largest nominal width of the distribution pipe DN in the current flushing section	25	32	40	50	65	80	100
Minimum number of draw-off points to be opened DN 15	2	4	6	8	12	18	28
 Jet regulators, sieves, flow regulators, hand-held sho Maintenance fittings (main shut-off device on each floor opened Sensitive valves, fittings and equipment have been researched been researche	and ot moved ng at th away f om the	her shu I and re e main rom the	t-off de placed shut-o e rising opened	wices) I with a ff valve pipe a l last) a	ave be daptore and m re fully II draw-	en fully s oving	
Start of the flushing process:							
End of the flushing process:							
Final steps: Built-in filters and strainers have been cleaned 							
The flushing of the drinking water system has been prop	erly ca	rried ou	ut.				
Place Date							

9.1 Quality assurance

All incoming goods that are intended for use as raw and auxiliary materials for further processing, are checked for their suitability by POLOPLAST Quality Assurance.

The manufacture of quality-controlled pipeline systems requires all necessary procedural steps:

- Monitoring
- Control
- Inspection

Furthermore, all results and procedures are documented.

The minimum requirements for independent company quality control are derived from the corresponding regulations for the quality control of sanitary pipeline systems, in that compliance must also include inspection by a neutral testing institution within the framework of external control.

External control, in addition to external testing of products, includes

- testing of the manufacturer's own required control measures
- examination of the technical equipment requirements
- hygienic and toxicological testing

External control of the POLO-ECOSAN Installation System in Germany is conducted by the

- Süddeutsches Kunststoffzentrum (Southern German Plastics Centre) (SKZ)
- Hygiene Institut (Hygiene Institute of) Karlsruhe (TZW),

which are authorised as testing centres by DVGW (German Association of Gas and Water Facilities), among others.

External control of approvals for foreign usage is conducted in a similar manner.

The suitability of the POLOPLAST pipe systems for drinking water has been established by the Technology Water Centre (TWZ) according to the "Guideline for Hygienic Assessment of Organic Materials in Contact with Drinking Water" (KTW Guideline) provided by the German Federal Environmental Agency, and is subject to permanent external control.

Summary of key points:

- The entire production process is defined, monitored, documented
- Quality management according to DIN EN ISO 9001
- Complies with all applicable standards, laws and regulations
- Monitoring by external institutes
- Certified system


INITIAL OPERATION

ASSEMBLY GUIDELINES


90.

Quality assurance

The entire production process for POLOPLAST pipe systems and fittings is monitored and controlled by POLOPLAST quality assurance. All results and procedures are documented. The monitoring is carried out by external institutes and by self-monitoring.







• Examination of the technical equipment requirements

• Hygienic and toxicological testing acc. to KTW guidelines

Our organisation is certified in accordance with ISO 9001 and ISO 50001





BLY WELDING NES TECHNOLOGY

TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

SYSTEM REQUIREMENTS

PLANNING AND DESIGN

9.1.1 Approvals

- Tested by the accredited testing institute SKZ
- Hygienically safe in accordance with the KTW guideline of the Federal Environmental Agency
- Compliance with standards according to EN ISO 15874
- Certified by DVGW and CSTB



9.1.2 Testing institutes for product monitoring and certification

qualityaustria

Erfolg mit Qualität

Das Kunststoff-Zentrum

tgm

Staatliche Versuchsanstalt





WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

9.2 POLO-ECOSAN Letter of guarantee



9.3 POLO-UV ML5 Letter of guarantee



TRANSPORTATION AND STORAGE

DRINKING WATER HYGIENE

WELDING TECHNOLOGY

ASSEMBLY GUIDELINES

INITIAL OPERATION

9.4 Sustainability

In the development of its products and their production, POLOPLAST places emphasis on the sustainable, environmentally friendly and resource-conserving implementation. The raw material polypropylene PP-R can be recycled to 100 %. Any residues from the production can be reused.

Thanks to this advantage it can be processed further for the industry in many different ways. Compared to other materials, the energy expenditure required for the production of POLOPLAST products is significantly lower. Furthermore, the process does not produce any environmentally hazardous substances, leading to an excellent environmental performance evaluation overall.

Advantages PP-R:

- Can be recycled
- Free of halogen
- Free of plasticisers
- Hygienically safe
- Environmentally friendly



NOTES

NOTES

NOTES



© Copyright. All contents and graphical representations are protected by copyright and, even in altered form, they may only be reproduced, published or distributed following the express written approval of POLOPLAST.

03/03.18/4.000_EN_wanted.co.at



POLOPLAST GmbH Kirnachstraße 17 87640 Ebenhofen . Germany T +49 (0) 8342 . 70 06.0 . F +49 (0) 8342 . 70 06.66

info@poloplast.com www.poloplast.com